

**SERIES NG 1700**  
**STRUCTURAL CONCRETE**

---

**Contents**

Clause	Title	Page	Clause	Title	Page
NG 1701	Concrete - Classification of Mixes	2	NG 1724	Prestressing Tendons - Tensioning	28
NG 1702	Concrete - Ordinary Structural - Constituent Materials	3	NG 1725	Prestressing Tendons - Protection and Bond	29
#NG 1703	Concrete - Special Structural - Constituent Materials	4	NG 1727	Inspection and Testing of Structures and Components	30
NG 1704	Concrete - General Requirements	5	NG	Sample Appendices	A1
NG 1705	Concrete - Requirements for Designed Mixes	12	<b>NATIONAL ALTERATIONS OF THE OVERSEEING ORGANISATIONS OF SCOTLAND, WALES AND NORTHERN IRELAND</b>		
NG 1706	Concrete - Production	13	<b>Scotland</b>		
NG 1707	Concrete - Compliance	13	Clause	Title	Page
NG 1708	Concrete - Surface Finish	15	NG 1703SE	(05/01) Concrete - Special Structural - Constituent Materials	S1
NG 1709	Concrete - Surface Impregnation	16	# denotes a Clause which has a substitute National Clause for one or more of the Overseeing Organisations of Scotland, Wales or Northern Ireland.		
NG 1710	Concrete - Construction General	18			
NG 1711	(05/01) Concrete - Grouting and Duct Systems for Post-tensioned Tendons	23			
NG 1712	(05/01) Reinforcement - Materials	25			
NG 1713	(05/02) Carbon Steel Reinforcement and Stainless Steel Reinforcement - Bar Schedule Dimensions - Cutting and Bending	26			
NG 1714	Reinforcement - Fixing	26			
NG 1715	Reinforcement - Surface Condition	26			
NG 1716	Reinforcement - Laps and Joints	26			
NG 1717	Reinforcement - Welding	27			
NG 1718	Prestressing Tendons - Materials	28			
NG 1719	Prestressing Tendons - Handling and Storage	28			
NG 1720	Prestressing Tendons - Surface Condition	28			
NG 1722	Prestressing Tendons - Cutting	28			
NG 1723	Prestressing Tendons - Positioning of Tendons, Sheaths and Duct Formers	28			

# STRUCTURAL CONCRETE

## NG 1701 Concrete - Classification of Mixes

### General

1 (05/01) In the Specification the concept of concrete as a single material has been adopted. It is therefore the responsibility of the designer to specify in Appendix 17/1 the type of concrete required to ensure both the strength and the durability of the finished structure.

### Designed Mix

2 The Contractor should be responsible for selecting the mix proportions in accordance with Clause 1705 to achieve the required strength and workability, but the designer is responsible for specifying the minimum cement content, maximum water/cement ratio and other properties required to ensure durability in accordance with Clause 1704.

### Designed Mix for Ordinary Structural Concrete

3 By the definition given in sub-Clause 1701.2 limitations on the constituent materials are already established and therefore the designer need only specify the following:

Designed Mix for Ordinary Structural Concrete	Specification sub-Clause
Class of concrete	1704.1
Minimum cement content	1704.2
Required type and class of cement	1703.1
Maximum water/cement ratio	1704.2

### Designed Mix for Special Structural Concrete

4 These concrete mixes include those using admixtures, those using cements other than in sub-Clause 1702.1, lightweight aggregates, heavyweight aggregates, etc and those specially designed to have a special property or to produce a particular surface finish which may place a restriction on the use of materials from Clause 1702. It is important, therefore, to specify the requirements in detail and, where possible, to state the reasons for any special requirements so that the Contractor can more fully appreciate the object of the work.

In appropriate circumstances any of the following information may be included, but great care should be

taken to ensure that the requirements specified do not conflict with each other:

Designed Mix for Special Structural Concrete	Specification sub-Clause
Class of concrete	1704.1
Minimum cement content	1704.2
Maximum water/cement ratio	1704.2
Required workability	1707.3
Maximum cement content	1704.3
Required type and class of cement	1703.1
Required source of special type of aggregate	1703.2
Required admixture	1703.4
Air entrainment required	1707.4
Minimum or maximum temperature of fresh concrete	1710.6 or 1710.7
Rate of sampling and testing	1707.2(i)
Other requirements	1707.1 and 1708.2

### Requirements for Fresh Concrete

5 (05/01) Unless specified otherwise the requirements for the concrete in the fresh or plastic state, particularly its workability (see sub-Clause 1707.3) should be selected by the Contractor. It may be necessary when working in cold or hot weather to control the temperature of fresh concrete (see sub-Clause 1710.6 or 1710.7).

Where the minimum dimension of concrete to be placed at a single time is greater than 600 mm and especially where the cement content is likely to be 400 kg/m<sup>3</sup> or more, measures to reduce the adverse affects of temperature, such as the selection of aggregates with low coefficients of thermal expansion or of a cement type with a slower release of heat of hydration, should be considered. In exceptional cases other measures to reduce the temperature or to remove evolved heat may be necessary.

## NG 1702 Concrete - Ordinary Structural - Constituent Materials

### Cement

1 (05/02) Where cements other than those complying with BS EN 197-1 CEM I are used, account should be taken of their properties and any particular conditions of use.

High alumina cement concrete does not appear in the Specification. Its use should only be considered in the most exceptional circumstances when the effects of conversion are fully taken into account.

The control of the colour of the pulverized-fuel ash using the Lovibond Comparator is only required to ensure a satisfactory colour to the concrete.

The Lovibond 2000 Comparator and disc reference no. 296570 may be obtained from Tintometer Ltd, Waterloo Road, Salisbury, Wiltshire.

The use of CEM I (Portland cement) blended with pulverized-fuel ash or ground granulated blastfurnace slag may increase concrete durability and resistance to both chloride ingress and sulfate attack. However, care should be taken due to possible delayed strength development and particular attention should be paid to curing in accordance with sub-Clause 1710.5.

### Aggregates

2 (i) General. The designer may specify the use of aggregates other than those specified in sub-Clause 1702.3 or 1703.2, including types or gradings not covered by the appropriate British Standards, provided that there are satisfactory data on the properties of concrete made with them.

When high strength concrete is required, the source as well as the type of aggregate may need careful selection based on the results of trial mixes.

Where it is known that any property of any aggregate is likely to have an unusual effect on the strength, density, shrinkage, moisture movement, thermal properties, creep, modulus of elasticity or durability of concrete made with it, the designer should take account of these factors in the design and workmanship requirements.

Aggregates having a high drying shrinkage, such as some dolerites and whinstones, and gravels containing these rocks produce concrete having a higher drying shrinkage than that normally expected. This can result

in deterioration of exposed concrete and excessive deflections of reinforced concrete unless special measures are taken.

For further information refer to BRE Digest 357, which, in particular, includes advice about the testing of drying shrinkage for aggregates with properties outside the limits appropriate to the shrinkage test described in BS 812 : Part 120.

When air cooled blastfurnace aggregate complying with BS 1047 is used, sampling and testing should be carried out at sufficiently frequent intervals to confirm the bulk density.

Despite initial compliance with the minimum density, substantial variation above this minimum can change the characteristics of the concrete mix if the weights of the aggregates are kept constant. If such variations occur, the mix should be adjusted to allow for them. Further advice on this subject can be obtained from the Building Research Establishment.

(ii) Nominal maximum size. The preferred nominal maximum sizes of aggregate are 40 mm and 20 mm, but if a smaller size is necessary it should be either 14 mm or 10 mm.

(iii) The requirement for daily testing of aggregates for chloride content is to provide a knowledge of the variability and to enable compliance with the requirements of Table 17/2 and sub-Clause 1704.6. Where continuous test data provide information for assessing long term variability, lower test frequencies should be adopted. For example, land-won aggregates with a typical chloride content of less than 0.01% should not require frequent assessment.

(iv) (05/01) Control of alkali silica reaction and sulfate attack in buried concrete exposed to sulfates. Where control of alkali silica reaction in accordance with sub-Clause 1704.6 or precautions against sulfate attack in accordance with sub-Clause 1704.7 are necessary aggregates should be classified in terms of alkali reactivity (see NG 1704.5) or carbonate content (see NG 1704.6(v)) respectively.

## #NG 1703 Concrete - Special Structural - Constituent Materials

### Cement

1 NG 1702.1 also applies.

### Aggregates

2 NG 1702.2 also applies to aggregates for special structural concrete. In addition the moisture content of lightweight aggregates can vary considerably, and values of up to 25% have been recorded. The use of a microwave oven may prove beneficial in quickly establishing the moisture content.

Lightweight aggregates may continue to absorb water from the mix and consideration may have to be given to allowing addition of water for workability.

It should be noted that the vibration characteristics of lightweight aggregate concrete may need special techniques to ensure good compaction and finishes.

### Admixtures

3 (i) (05/01) General. Admixtures should be specified by type and effect.

Admixtures should never be regarded as an alternative to good concreting practice and should never be used indiscriminately.

Many admixtures are highly active chemicals and may impart undesirable as well as desirable properties to the hardened concrete; their suitability should generally be verified by trial mixes. The trial mix should contain cement of the same make and type and from the same source as that intended to be used for the Permanent Works. If two or more admixtures are thought to be required in any one mix, the manufacturer of each should be consulted. The trials should confirm that the admixture is compatible with all the other constituents of the concrete mix and show whether it accelerates or retards the setting time and results in any loss of workability.

Only in exceptional circumstances, for example in hot weather, should retarders be used in structural concrete. Consideration may be given to their use in grouts for prestressing tendons, especially in hot weather (see NG 1711.1).

(ii) (05/02) Air-entraining agents. Air-entraining agents used to entrain controlled percentages of air in the concrete generally improve its

durability and in particular its resistance to damage caused by freezing and thawing.

When a concrete of Grade 40 or lower is subject to freezing when wet and/or subject to the effects of salt used for de-icing, it should contain entrained air.

For special structural concrete containing entrained air, the addition of 1% air content to the mix can reduce the compressive strength of the concrete by approximately 5%, but if the water/cement ratio is reduced to take account of the improved workability, the cement content may be kept constant for up to 5% air entrainment with only marginal loss of strength.

The carbon contained in pulverized-fuel ash and certain pigments can substantially reduce the effectiveness of some air-entraining agents. This does not usually create a problem but care may have to be taken when using these materials. In some cases it may be necessary to increase appreciably the amount of agent used. The amount of air entrained in a concrete mix can also be affected by many other factors, among which are:

- Type and amount of admixture used.
- Consistency of the mix.
- Mix proportions.
- Type and grading of the aggregate.
- The length of time for which the concrete is mixed.
- Temperature. In the range 10°C to 30°C an increase of 10°C can reduce the amount of entrained air by about 25%.
- The cement type, source, fineness and cement content of the mix.

Recommended average air contents of fresh concrete should be maintained within the limits specified irrespective of mixing time and temperature (see NG 1707.5).

Entrained air will increase the cohesiveness of fresh concrete and this should be taken into account in the design of the mix and in the placing and compaction of the concrete.

## NG 1704 Concrete - General Requirements

### General Considerations

1 The minimum requirements for the strength and durability of the concrete in the hardened state should be decided by the designer from consideration of BS 5400 : Part 4, and the guidance in NG 1704.2, but if in addition a special property or a particular surface finish is required, these minimum requirements may have to be considerably exceeded.

The grade of concrete required depends partly on the particular use and the characteristic strength needed to provide the structure with adequate ultimate strength and partly on the exposure conditions and the cover provided to any reinforcement or tendons (see BS 5400 : Part 4).

### Minimum Cement Content and Maximum Water/Cement Ratio

2 (05/01) The designer should state in Appendix 17/1 the minimum cement content required for each concrete mix. One of the main characteristics influencing the durability of any concrete is its ability to absorb water. With strong dense aggregates, a suitably low absorption is achieved by having a sufficiently low water/cement ratio, by ensuring sufficient hydration of the cement through proper curing methods, and by ensuring maximum compaction of the concrete. Therefore for given aggregates the cement content should be sufficient to provide adequate workability with a low water/cement ratio so that the concrete can be fully compacted with the means available.

Water reducing admixtures complying with sub-Clause 1703.4 can be beneficial in reducing the free water/cement ratio.

Table NG 17/1 gives the minimum cement content required, when using a particular size of aggregate and maximum water/cement ratio to provide acceptable durability under the appropriate conditions of environment. This table applies to concrete made with cements described in sub-Clauses 1702.1 and 1703.1. The cement contents may need to be greater than the minimum values given in Table NG 17/1 when trial mixes (see NG 1705.2) indicate that this is necessary for:

- (i) the consistent production of a concrete with a maximum free water/cement ratio not greater than that given for a particular condition; and
- (ii) (05/02) the conditions of placing and compaction.

For information on minimum cement contents and maximum water/cement ratios and particular types of cement to provide a concrete having acceptable durability under exposure to a particular degree of sulfate or acid attack, reference should be made to BRE Special Digest SD1.

It should be noted that when referring to BRE Special Digest SD1 the requirements of Table NG 17/1 also apply.

### Maximum Cement Content

3 Cement contents in excess of 550 kg/m<sup>3</sup> should not be used unless special consideration has been given in design to the increased creep, risk of cracking due to drying shrinkage in thin sections, and higher thermal stresses in thicker sections. For higher grades of lightweight aggregate concrete, cement contents in excess of 550 kg/m<sup>3</sup> may be used provided that the concrete produced is suitable in all respects.

### Maximum Sulfate Content

4 Sulfates are present in most cements and in some aggregates; excessive amounts can cause expansion and disruption in the concrete.

### Control of Alkali-Silica Reaction

- 5 (i) (05/01) It is generally accepted that alkali-silica reaction can only occur if reactive minerals are present, the alkali level of the concrete is above a certain level and a sufficient supply of water is available. For concrete highway structures it must be assumed that sufficient water will be available so that aggregate types and alkali levels must be controlled. Most cases of alkali-silica reaction appear to be associated with the use of high alkali cements.
- (ii) Prior to acceptance of an aggregate as low, normal or high reactivity a report by an independent, qualified geologist should be obtained following examination of all types of material that the proposed source will yield during the construction of the Works. Samples from boreholes may be required and over long periods, more than one report.

The geologist should be experienced in the identification of aggregate constituents and is recommended to be a member of the Proficiency Scheme for Aggregate Petrographers (PSAP) and a Chartered Geologist.

- (iii) The requirements of sub-Clause 1704.6 are based on the guidance given in Building

Research Establishment BRE Digest 330 Parts 1 - 4, except that the use of high alkali content cements is restricted to use in combination with prescribed quantities of ggbs and pfa.

- (iv) (05/02) It should be noted that for CEM I (Portland cement), ggbs or pfa the alkali determination has to be carried out on the individual material before blending or intergrinding.
- (v) When alkali-silica reaction is being controlled by the limitation of sodium oxide

equivalent, any sodium ion present in the aggregate has to be included in the total sodium oxide equivalent. This should be done by including 0.76 times the chloride ion content of the aggregate in the mix. The factor of 0.76 allows for the chloride ions present being associated with metals other than sodium.

- (vi) The possible effect on the Permanent Works of alkali-silica reaction in Temporary Works concrete left in place should be considered.

**TABLE NG 17/1: Minimum Cement Content (kg/m<sup>3</sup>) and Maximum Water/Cement Ratio Required in Concrete to Ensure Durability**

Environment		Prestressed Concrete				Max free water/cement ratio	Reinforced Concrete				Max free water/cement ratio	Plain Concrete				
		Nominal maximum size of aggregate (mm)					Nominal maximum size of aggregate (mm)					Nominal maximum size of aggregate (mm)				
		40	20	14	10		40	20	14	10		40	20	14	10	
Concrete surfaces exposed to: (i) abrasive action by sea water (ii) water with a pH 4.5 or less	Extreme	320	350	370	390	0.45	320	350	370	390	0.45	320	350	370	390	0.50
Concrete surfaces directly affected by: (i) de-icing salts (ii) sea water spray	Very Severe	300	325	345	365	0.45	295	325	345	365	0.45	295	325	345	365	0.50
Concrete surfaces exposed to: (i) driving rain (ii) alternate wetting and drying	Severe	300	325	345	365	0.50	295	325	345	365	0.50	270	300	320	340	0.50
Concrete surfaces above ground level and fully sheltered against all of the following: (i) rain (ii) de-icing salts (iii) sea water spray Concrete surfaces permanently saturated by water with a pH greater than 4.5	Moderate	300	325	345	365	0.50	270	300	320	340	0.50	245	275	295	315	0.50

(05/01) **Buried concrete exposed to sulfates**

- 6 (i) (05/02) The requirements to protect buried concrete exposed to sulfates are based on Building Research Establishment Special Digest SD1 'Concrete in Aggressive Ground' (published in four Parts by BRE in August 2001). The recommendations to SD1 extend those in the Report of the Thaumate Expert Group in respect of sulfate attack in order to rationalise, and give further options for, precautions to minimise the risk of the occurrence of the thaumasite form of sulfate attack (TSA), as well as the conventional ettringite form of sulfate attack. BS 5328:1997 is being amended to align with SD1. As in previous guidance, the precautions take the form of concrete mix design options with, where appropriate, Additional Protective Measures. The concrete mix options (Table 17/4) are now dependent upon a parameter termed the Design Chemical (DC) Class. The DC Class is derived as follows:
- (a) An initial classification of the sulfate conditions is made from analysis of the sulfate content of the soil and/or groundwater samples, taking into account the possibility of oxidation of sulfides to sulfates and the magnesium ion concentration and, for brownfield sites with  $\text{pH} < 5.5$ , chloride and nitrate ions. This gives the Design Sulfate Class.
  - (b) Account is then taken of the type of ground (natural or brownfield), the mobility of the groundwater and its pH to give the Aggressive Chemical Environment for Concrete (ACEC) classification for the site (Table 17/5).
  - (c) The ACEC classification is then considered together with the Structural Performance Level (Table 17/6) required for the structure, the thickness of the concrete element and other factors (such as any hydrostatic head or surface carbonation of the concrete) to determine the basic Design Chemical Class and the number of Additional Protective Measures (APM) needed (Table 17/7). It should be noted that Parts 3 and 4 of BRE Special Digest SD1 provide a simplified alternative to this generic procedure for determining the Design Chemical Class and the number of APM by giving a series of Design Guides. Part 3 of SD1 gives Design Guides for common applications of concrete, including foundations and elements for transport structures, whilst the Design Guides in Part 4 are for specific precast products, including pipeline systems, segmental linings for tunnels and shafts, and box culverts.
- (d) Each Design Guide is limited to a particular type of concrete construction and, where appropriate, hydrostatic and carbonation conditions. Each Design Guide has a recommended Structural Performance Level associated with it and gives the recommended DC Class and number of APM for each ACEC Class as well as, where appropriate, specific design notes.
  - (e) Having determined the DC Class and number of APM, by either the generic procedure or via the Design Guides, it is then necessary to choose from the options for APM (Table 17/8), which may require a modification to the DC Class, and then to consider the Aggregate Carbonate Range of available aggregates (Table 17/9). As part of the procedure for avoiding the thaumasite form of sulfate attack, the combined aggregate is classified into an Aggregate Carbonate Range according to its 'calcium carbonate equivalent' content. Range A aggregates are high in carbonate, Range B medium and Range C low.
  - (f) The DC Class is specified, together with any restrictions on the aggregate or cement types (Table 17/10). The concrete qualities to resist chemical attack, in terms of minimum cement content and maximum w/c ratio, are given for each DC Class and, where appropriate, for different Aggregate Carbonate Ranges and different cement or combination types, in Table 17/4.
- (ii) (05/02) The specific measures incorporated to minimise the risk of TSA are:
- Classification of ground containing sulfides allowing for the potential increase in sulfate/acidity which could result from oxidation of sulfides if the ground is disturbed eg by backfilling.

- Modification of mix design of concrete to be placed in Design Chemical Class 3 and above depending on the carbonate content of the aggregate.
  - Introduction of Additional Protective Measures in the structural design and/or modifications to the concrete mix on the basis of Design Chemical the ACEC Class and the Structural Performance Level required for the structure.
- (iii) (05/02) For all forms of sulfate attack the following primary risk factors are necessary:

- Presence of soluble sulfates and/or oxidisable sulfides in the ground.
- Presence of groundwater, presenting a greater risk if mobile or highly mobile.

Additionally, for TSA the following primary risk factors are also necessary:

- Presence of carbonate, generally in the concrete aggregates.
- Low temperatures (generally below 15°C).

The following secondary factors influence the occurrence and severity of sulfate attack and these are the basis of the requirements in 1704.7.

- Type and quantity of cement in the concrete.
- Quality of the concrete (w/c ratio, compaction).
- Changes to ground chemistry and water regime resulting from construction activities.
- Type, depth and geometry of buried concrete.

(05/02) **The classification of ground for ACEC Class**

- (iv) (05/02) This should be undertaken in accordance with the procedures and test methods detailed in Part 1 of BRE Special Digest SD1. Two principal stages are involved:

Firstly, determination of the Design Sulfate Class from the sulfate content of the groundwater and/or a 2:1 water:soil extract, and the magnesium ion concentration. It is important to note that in the case of disturbed ground containing sulfides, such as pyrite, the ground should be classified taking

into account the potential sulfate content which could be produced by oxidation of such sulfides.

Secondly, determination of the ACEC Class from the Design Sulfate Class, the type of site (natural or brownfield) and the mobility and pH of the groundwater. Assignment of the groundwater as static, mobile or highly mobile is of paramount importance and guidance is given in Part 1, Section 4 of SD1. Specific procedures are given in SD1 for determining the ACEC Class for brownfield sites, for sites where disturbance of pyrite-bearing ground could result in additional sulfates and, more simply, for all other sites. It should be noted that, for the purposes of SD1, a brownfield site is defined as one that has been subject to former industrial development or waste deposition, and which may contain aggressive chemicals in surface waste accumulations or in ground penetrated by leachates.

The ACEC site classifications are given in Table 17/5. Specific points to note in the ACEC Class nomenclature are that ACEC Classes with a suffix s indicate static groundwater and no Additional Protective Measures are generally necessary, Classes with a suffix m relate to the higher levels of magnesium in Design Sulfate Classes 4 and 5, whilst classes with a suffix z indicate where the concrete has primarily to resist acid conditions.

After determination of the ACEC Class for the site it is used with the Structural Performance Level required for the structure and knowledge of the concrete section thickness to determine the Design Chemical Class and the required number of Additional Protective Measures in accordance with Table 17/7 or the Design Guides given in Parts 3 and 4 of SD1.

**Structural Performance Level**

- (v) (05/02) The Structural Performance Level of the structure should be assessed in terms of its design service life, criticality of use and structural vulnerability. Three levels have been defined: low, normal and high. Typical attributes are given in Table 17/6. Foundations to Highways Agency and other UK Overseeing Organisations' permanent structures are generally designed for 120 year life and should be classed as high performance level.



(05/02) **Additional Protective Measures**

(vi) The options for Additional Protective Measures are given in Table 17/8. Further details are given in Part 2, Section 5 of SD1. Where enhanced concrete quality is selected as an APM, this can be satisfied by increasing the concrete quality requirements (ie minimum cement content and maximum w/c ratio) by one DC Class (see footnote 4 of Table 17/4). This APM may be applied twice where there are a sufficient number of higher DC Classes to move into. Where a 'starred' DC Class is given, (see Specification of Concrete below), the enhancement step is to a similarly-starred higher DC Class, eg DC-3\*\* with a one-step enhancement of concrete quality leads to a specification of DC-4\*\*. An enhancement of the number of APM may be required where there is a hydrostatic head of groundwater greater than five times the concrete section thickness, whilst a relaxation of one APM or one DC Class may be permitted where the concrete has surface-carbonated prior to exposure to sulfates (see footnotes to Table 17/7). These adjustments are automatically accounted for in the Design Guides in Parts 3 and 4 of SD1. All APM should be included in the Works and the final DC Class after any enhancement or relaxation should be specified to the Contractor or to the Concrete Producer.

**Carbonate range of aggregates**

(vii) (05/02) For Design Chemical Classes DC-3, DC-3\*, DC-3\*\*, DC-4, DC-4\*, DC-4\*\*, DC-4m, DC-4m\* and DC-4m\*\*, concretes in contact with the ground made with any aggregates containing significant quantities of carbonates should be designed to resist TSA. Aggregate materials requiring particular consideration include coarse and fine crushed limestones (including dolomite) and limestone gravels. However, other types of aggregate, such as mixed sands and gravels and recycled aggregates, may also contain varying quantities of carbonates, including particles of limestone and shell fragments.

For the purposes of minimising the risk of damage from TSA, carbonate bearing aggregates are classified into Ranges A, B and C. These ranges are defined graphically in Table 17/9 and used in Table 17/4.

- **Range C** aggregates have the lowest carbonate content and concretes containing such aggregates will not in general be prone to TSA, even when the ground has a relatively high sulfate classification.
- **Range B** aggregates have a higher proportion of carbonates.
- **Range A** aggregates may contain an unlimited proportion of carbonates but concrete mix requirements are more onerous in Design Chemical Class DC-3 and above (Table 17/4), except for DC-3z and DC-4z for which no distinction between Aggregate Carbonate Ranges is made. Similarly, no distinction between cement types is made in these DC Classes. The reason for this is that in DC Classes with a suffix **z**, the concrete is primarily required to resist acid, rather than sulfate, conditions. Since the rate of erosion of concrete surfaces in acidic conditions is affected less by the Aggregate Carbonate Range or the type of cement than by the quality of the concrete, no limitations on Aggregate Carbonate Range or the type of cement to resist acidic conditions are given.

In practice the best way to determine the carbonate content of aggregates is by the measurement of the CO<sub>2</sub> evolved when it is treated with acid. This will cater for all types of carbonates including dolomite. By multiplying the measured percentage amount of CO<sub>2</sub> by 100/44 (the ratio of the respective molecular masses) it is possible to determine the 'CaCO<sub>3</sub> equivalent' content. A possible test procedure for CO<sub>2</sub> determination (primarily intended for use on cement but which could be adapted) is given BS EN 196-21 : 1992.

This approach also caters for carbonate aggregate containing dolomite. However, it should be noted that when the aggregate consists entirely of dolomite, the calcium carbonate equivalent mass will be 108.6% of total mass of aggregate. Therefore, in Table 17/9 y-axis values up to and including this value are acceptable and correspond to Range A carbonate levels.

### Specification of concrete

- (viii) (05/02) Having established the final DC Class (after any enhancement or relaxation), the concrete requirements can now be identified according to Table 17/4. Depending on the aggregate Range (A, B or C) and cement type, different concrete mixes and concrete parameters are recommended. Well compacted, low water/cement ratio concrete appears to be more resistant to deterioration caused by sulfate attack. It is therefore important that conformity with both the minimum cement contents and maximum water/cement ratios is maintained in accordance with one of the methods specified in BS 5328 : Part 4 : Clauses 3.13 and 3.14. The use of water-reducing admixtures may be necessary, especially where the low maximum w/c ratios associated with the use of Range A aggregates are specified. Where a DC Class of DC-3, DC-4 or DC-4m is given or derived, the number of APM may be reduced (provided that the reduction does not override the recommendation to use or include surface protection) by: one provided that DC-3\*, DC-4\* or DC-4m\* concrete is specified; two provided that DC-3\*\*, DC-4\*\* or DC-4m\*\* concrete is specified. It can be seen from Table 17/4 that the single-starred classes require the use of Range B aggregates (Range C may also be used) and the double-starred classes require the use of Range C aggregates only.

### Design of concrete for piles

- (ix) (05/02) Design of concrete for piles will need careful consideration if ground assessment indicates a high ACEC Class, particularly so if required for high performance structures in which the piles are required to resist tension forces or horizontal loads which create bending moments. In adverse situations the design of the piles must be carefully appraised, and additional precautionary measures such as the use of Range C aggregate concrete or sleeving considered.
- In general, precast and in-situ concrete piles through natural undisturbed unweathered sulfide/sulfate-bearing ground appear to carry little risk of deterioration by sulfate attack. An exception may be cases where the unweathered ground has seepage paths through discontinuities or more permeable zones and there is a flow of groundwater through these which has a high concentration

of sulfate derived from a source such as the gypsum present in Mercia Mudstone.

In the case of concrete piles in contact with well-weathered sulfate-bearing clay (such clay is generally free from sulfides such as pyrite), the outer surface should be regarded as at some risk of sulfate attack particularly if ground conditions are wet. Such attack could potentially reduce the skin friction component of pile load-bearing capacity. The concrete design should be based on the results of a thorough ground appraisal that determines sulfate concentrations at appropriately close vertical intervals (say 1 metre apart).

In-situ concrete piles through 'made' ground may be especially vulnerable to sulfate attack. Waste materials from mining and industry are often rich in sulfides and sulfates. Also, made ground composed of formerly unweathered pyrite-rich clay may potentially have high sulfate contents due to oxidation and bacterial processes. Thorough ground appraisal is needed prior to concrete design. Appropriate procedures are given in Part 1 of SD1 and Highways Agency Standard HD 22 'Ground Investigation and Earthworks - Procedure for Geotechnical Certification'. Effects on inadequately specified concrete piles could include significant reduction in pile section and corrosion of reinforcement, as well as loss of skin friction.

### Drainage considerations

- (x) (05/02) Sulfate and/or acid bearing groundwater should be intercepted, if possible, before coming into contact with buried concrete, and backfill must be adequately drained. Structure-specific and carrier drains in proximity to the structure or building foundations should be designed to ensure that they have sufficient capacity and that they can be maintained. Detailing of the design of drainage and its construction should be undertaken with care to avoid accidental discharge of contaminated water into backfill to structures, or on to buried concrete surfaces.

Specifically designed groundwater drainage is the preferred Additional Protective Measure where a hydrostatic head of groundwater greater than five times the concrete section thickness is present (see footnote 2 to Table 17/7).

### Carbonation of concrete

- (xi) (05/02) All concretes are potentially susceptible to varying degrees of attack by soluble sulfates and acids present in groundwater. Precast concrete elements, air-dried after a period of moist curing, appear to be less susceptible to sulfate attack than cast in-situ concrete elements. At present, this is attributed to carbonation of the surface layers. Leaving cast in-situ concrete exposed to the atmosphere for several weeks before backfilling may reduce the risk of sulfate attack, although limited field evidence has shown that thaumasite can form behind an intact carbonated layer. If air-drying is adopted, this should be considered as a secondary treatment after normal curing methods have been undertaken. Where it is considered as a practical option, groundwater runoff should be intercepted before coming into contact with the concrete.

The recommendations of SD1 recognise the potential benefits by permitting a reduction of one DC Class or one APM where surface carbonation before exposure to sulfates can be assured. However, concrete is unlikely to carbonate significantly over a period of several weeks unless protected from rainfall. Since carbonation does not protect against acid attack, this relaxation is not permitted for ACEC Classes with a suffix z.

### Sulfates resulting from sulfides in the ground

- (xii) (05/02) The risk of deterioration due to sulfate attack, including TSA is worse where clays or other sulfide bearing materials have been excavated, reworked and replaced adjacent to buried concrete. The rapid oxidation of sulfides, particularly pyrites, in disturbed ground, results in enhanced levels of sulfates in the soil and groundwater.

Careful consideration must be given to the choice of materials surrounding buried concrete. They must be assessed in relation to the presence and source of sulfates, the prevailing groundwater conditions, the provision and location of drainage, the proposed usage of the structure, and coatings and other protective measures to be used. Though there may be benefits in considering the use of non-sulfate/sulfide bearing backfills in proximity to structures, designers would need to assess the potential for sulfate

migration from remote sources through the backfill.

Large excavations to deep foundations create sumps around buried concrete. If they are unavoidable then account should be taken of the more aggressive groundwater conditions and steps taken to provide adequate drainage to the backfilled excavation and to prevent groundwater entering from the surrounding area. On no account should such excavations be refilled with clays containing high concentrations of sulfates and sulfides.

Irrespective of the type of backfill, designers should try to ensure that groundwater is intercepted by drains or other means to prevent groundwater reaching buried concrete.

### Surface protection

- (xiii) (05/02) Surface protection is required as an Additional Protective Measure for ACEC Classes AC-5, AC-5m and AC-5z, as well as in AC-4z where the concrete section thickness is less than 140 mm (see Table 17/7).

At present there is little information available on the protection afforded by commercially available coatings and tanking against sulfate attack. Traditional methods of using bitumen emulsion based coatings have not been fully effective in all the cases of TSA investigated so far. However, such coatings, properly applied, appear to offer some measure of additional protection, and are an acceptable additional protective measure.

The main requirements of coatings and tanking are listed below:

- provide an impermeable barrier;
- be resistant to sulfates and other deleterious chemicals;
- have a neutral effect on the concrete substrate;
- be resistant to envisaged mechanical damage;
- be easy to apply correctly;
- have long term durability;
- be cost effective.

Such coatings and tanking must be applied in accordance with the manufacturer's instructions, and the workmanship must be of a high standard to maintain their integrity.

As an alternative to commercial coatings and tanking, there appears to be some merit in considering the use of additional 'sacrificial' concrete in buried construction. This could be achieved by providing an additional sacrificial thickness of cover concrete integral with parent concrete or by constructing a separate layer of concrete made from Range C aggregates.

A sacrificial concrete layer is one of the Additional Protective Measures given in Table 17/8. The quality of such a layer should be at least equal to that of the inner concrete. Although service data are scarce, SD1 (Part 2, Section 5.6) suggests an additional sacrificial layer of 50 mm thickness. The design of the concrete element would need to be reappraised to reflect the additional concrete.

Where TSA is considered possible, the need to exercise good control over the maintenance of the design cover in reinforced concrete construction is emphasised to minimise the risk of, and delay the onset of, reinforcement corrosion.

#### Options for concrete mixes

- (xiv) (05/02) Where possible designers should include all options for concrete mixes in each Design Chemical Class in Contracts to allow Contractors to price alternatives in the tender process. These options may also include different drainage, surface protection or other measures as part of the package to minimise the risk of TSA.

An alternative approach, which would be favoured, is to use a 'Designated Outline', for a Contractor based design, offering a complete 'package' of measures to minimise the risks of TSA. A typical package would consist of a concrete mix to comply with the requirements of Table 17/4, including any enhancement of concrete quality applied as an Additional Protective Measure in accordance with Table 17/8, and where necessary, further Additional Protective Measures, ie surface protection, a sacrificial concrete layer, the use of controlled permeability formwork or drainage. If this approach is adopted then the compiler of the Contract documentation must include sufficient information about the design constraints and ground conditions to allow tenderers a fair opportunity to submit their detailed proposals and price the package. For

this purpose NG Sample Appendix 17/5 should be completed for each structure or group of structures in respect of buried or partially buried concrete.

### NG 1705 Concrete - Requirements for Designed Mixes

#### Evidence of Suitability of Proposed Mix Proportions

1 (05/01) Evidence should be available for each grade of concrete showing that, at the intended workability, the proposed mix proportions and manufacturing method will produce concrete of the required quality. The target mean strength should normally exceed the specified characteristic strength by at least the current margin.

Mix proportions having the required minimum cement content proposed by the producer of a particular lightweight aggregate as complying with the strength requirements of Grades 15, 20, 25 or 30 may be accepted in lieu of trial mixes where it is demonstrated that the results can be achieved. For higher grades of concrete, trial mixes should be made. Where lightweight concrete is used the maximum permissible wet density should be specified.

For ready mixed concrete the supplier will, if required, provide the current control value of standard deviation indicated by the supplier's control system and the number of results when less than 100 have been assessed. The range of results permitted by an accepted product certification scheme for ready mixed concrete (Appendix B), to be used in the calculation of standard deviation should be deemed to satisfy the requirement for tests to be made on concrete of 'nominally similar proportions'.

At a given level of control and above a characteristic strength of 20 N/mm<sup>2</sup> the standard deviation of mixes made from similar materials is sensibly constant and independent of cube strength.

#### Trial Mixes

2 If trial mixes are required to demonstrate that the maximum free water/cement ratio is not exceeded (see NG 1704.2) two batches should be made in a laboratory with cement and surface dry aggregates known to be typical from past records of the suppliers of the material. The proposed mix proportions should not be accepted unless both batches have a free water/cement ratio below the maximum specified value at the proposed degree of workability. For this purpose existing laboratory test reports may be accepted instead of trial mixes only if the materials to be used in the

structural concrete will be similar to those used in the tests. The workability of a trial mix should be checked by casting a trial panel representing the most congested part of the work (see NG 1708.1).

## NG 1706 Concrete - Production

### General

1 Every reasonable opportunity and facility should be taken to inspect the materials and the manufacture of concrete and to take any samples or to make any tests. All such inspection, sampling and testing should be carried out with the minimum of interference with the process of manufacture and delivery.

### Aggregate

2 Separate sands (ie fine aggregates) and coarse aggregates should be used except for Grades 7.5, 10 and 15, where all-in aggregate may be used. For grades of concrete other than 7.5, 10 and 15, the grading of each size of aggregate from each pit, quarry or other source of supply should be determined at least once weekly. The results of such tests should be used to check whether the gradings are similar to those of the samples used in the establishment of the mix proportions. The results of routine control tests carried out by the aggregate producer may be acceptable for this purpose.

### Batching and Mixing

3 (05/01) The mixing time should be not less than that used by the manufacturer in assessing the mixer performance. In the case of mixes of low workability or high cement content, this may not ensure maximum strength, and it may be advisable to determine a satisfactory mixing time by comparing the strength of samples mixed for different times.

It is advisable to check the accuracy of the batching plant measuring equipment at intervals not exceeding 1 month.

The water content of each batch of concrete should be adjusted to produce a concrete of the workability established for the trial mix.

Allowances should be made in the calculation of cement content for the transportation of the concrete within cleaned lorries or other suitable vessels.

### Control of Strength of Designed Mixes

4 (i) Adjustments to mix proportions. During production, adjustments of mix proportions will normally be made in order to minimize the variability of strength and to approach

more closely the target mean strength. Such adjustments are regarded as part of the proper control of production, but the specified limits of minimum cement content and maximum water/cement ratio should be maintained. Changes in cement content may have to be declared (see NG 1705.1).

- (ii) (05/01) Change of current margin. A change in the current margin used for judging compliance with the specified characteristic strength becomes appropriate when the results of a sufficiently large number of tests show that the previously established margin is significantly too large or too small. Recalculation of the margin should be carried out in accordance with sub-Clause 1705.1, but although a recalculated margin is almost certain to differ numerically from the previous value, the adoption of the recalculated value is not generally justified if the two values differ by less than 18% when based on tests on 40 separate batches, or less than 11% when based on tests on 100 separate batches, or less than 5% when based on tests on 500 separate batches.
- (iii) (05/01) Additional Water. The addition of extra water to a properly designed concrete mix will not only increase the slump, but will also increase the shrinkage potential and permeability of the hardened concrete. The extra water will also reduce the final compressive strength of the concrete and its durability.

## NG 1707 Concrete - Compliance

### General

1 Provided that the materials used are in accordance with Clauses 1702 or 1703 and that correct methods of manufacture (see NG 1706) and practices of handling raw materials and manufactured concrete have been used, the compliance of:

- (i) a designed mix for ordinary structural concrete should be judged by the strength of the hardened concrete in comparison with the specified characteristic strength (see NG 1707.2), together with the cement content in comparison with the specified minimum (see NG 1707.3);
- (ii) a designed mix for special structural concrete should be judged in a manner

similar to (i) above except that, in addition when it is applicable, compliance with any specified special requirements should be judged by the standards set out in sub-Clauses 3, 4, 5 and 6 of this Clause.

When the designer specifies “other requirements” in Appendix 17/1 (eg density or modulus of elasticity of concrete), compliance with those requirements should be determined from a detailed description of the method of test and with tolerances that take appropriate account of variability due to sampling, testing and manufacture, which the designer should describe in Appendix 17/1.

### Strength

- 2 (i) (05/02) General. The rate of sampling should be as specified in Table 17/11 of the Specification. Higher rates of sampling and testing may be required at the start of work to establish the level of quality quickly or during periods of production when quality is in doubt; conversely, rates may be reduced when high quality has been established.

For special reinforced concrete such as end blocks or hinges the rates of sampling for prestressed concrete may be considered more appropriate.

- (ii) Testing. The testing specified in sub-Clause 1707.2 (ii) should be the normal method of testing concrete production. It achieves a good balance between the risk of incorporating concrete that does not meet the strength requirements and the risk of rejecting satisfactory concrete.
- (iii) Special testing. This should be called up for single batches of concrete, for limited production runs or where the designer requires assurance that the concrete placed in a particular part of the Works is of adequate strength. It should not, however, be applied to every batch as this would be expensive and would provide no better overall assurance than normal testing.
- (iv) (05/01) Non-compliance. When the average strength of four consecutive test results fails to meet the requirements of sub-Clause 1707.2(ii), the mix proportions of subsequent batches of concrete should be modified to increase the strength.

The action to be taken in respect of the concrete that is represented by the test

results that fail to meet the requirements of sub-Clause 1707.2(ii) or (iii), may range from qualified acceptance in less severe cases to rejection and removal in the most severe cases. In determining the action to be taken, due regard should be given to the technical consequences of the kind and degree of non-compliance, and to the economic consequences of alternative remedial measures either to replace the substandard concrete or to ensure the integrity of any structure in which the concrete has been placed.

In estimating the concrete quality and in determining the action to be taken when the tests indicate non-compliance, the following should be established wherever possible:

- (a) the validity of the test results, and confirmation that specimen sampling and testing have been carried out in accordance with BS 1881;
- (b) the mix proportions actually used in the concrete under investigation;
- (c) the actual section of the structure represented by the test cubes;
- (d) the possible influence of any reduction in concrete quality on the strength and durability of this section of the structure.

Additional tests may be carried out on the hardened concrete in the structure to confirm its integrity or otherwise. These may include non-destructive testing methods or the taking of cored samples (see NG 1727) for laboratory examination and testing.

### Cement Content

- 3 The observation of batching is one way of ensuring that the correct cement content is maintained.

As an alternative the cement content may be determined from samples representative of any batch of concrete, provided that a suitable testing regime is used to measure the cement content of fresh concrete to an accuracy of  $\pm 5\%$  of the actual value with a confidence of 95%.

### Water/Cement Ratio

- 4 The ability to comply with the maximum free water/cement ratio specified in the Contract, at a suitable level of workability, will have been determined by means of trial mixes. Provided that the constituent materials and mix proportions are not substantially

different from those used in the trial mixes, the water/cement ratio may be judged from workability tests.

As an alternative the water/cement ratio may be determined from samples representative of any batch of concrete, provided that a suitable testing regime (including errors due to sampling) is used to measure the water/cement ratio of fresh concrete to an accuracy of  $\pm 5\%$  of the actual value with a confidence of 95%.

### Air Content of Fresh Concrete

5 It should be noted that the method of measuring air content described in BS 1881 is not applicable to concrete made with lightweight aggregate.

### Additional Tests on Concrete for Special Purposes

6 Additional cubes may be required for various purposes. These should be made and tested in accordance with BS 1881, but the methods of sampling and the conditions under which the cubes are stored should be varied according to the purpose for which they are required. For determining the cube strength of prestressed concrete before transfer or of concrete in a member before striking formwork or removing cold weather protection, sampling should preferably be at the point of placing, and the cubes should be stored as far as possible under the same conditions as the concrete in the members. The extra cubes should be identified at the time of making and should not be used for the normal quality control or compliance procedures.

## NG 1708 Concrete - Surface Finish

### General

1 (05/03) The type of surface finish required depends on the nature of the member, its final position in the structure, and whether or not it is to receive an applied finish. The appropriate finish, which may vary from face to face, should be carefully chosen and clearly specified.

Wherever possible, samples of surfaces of adequate size (preferably incorporating a horizontal and vertical joint and reinforcement representative of heavily congested zones of reinforcement) should be agreed before work commences. All the factors affecting the quality of the surface finish from formwork should be carefully studied. For detailed descriptions of these factors and their interrelationship, attention is directed to the pamphlet 'Appearance Matters 3 The Control of Blemishes in Concrete', Cement and Concrete Association.

Texture, colour and durability are affected by curing (see NG 1710.5). Where appearance is important,

curing methods and conditions including the time of removal of formwork require careful consideration. Components that are intended to have the same surface finish should receive the same treatment.

### Control of Colour

2 Where uniformity of colour is important, all materials should be obtained from single consistent sources. In formwork the replacement of individual plywood sheets or sections of timber in large panels should be avoided.

Colour can be affected by curing.

### Release Agents

3 (05/01) Release agents for formwork should be carefully chosen for the particular conditions they are required to fulfil. Where the surface is to receive an applied finish, or it is to be impregnated, care should be taken to ensure the compatibility of the release agent with the subsequent treatment process, for example no deleterious residue should be left.

### Surface Finishes for Concrete

4 (i) The class of finish should be shown on the Drawings. Class F1 finish should be specified for unexposed formed surfaces and Class F2 finish normally for exposed surfaces. F3 finish is very costly and should only be used for small areas. F4 is appropriate where large areas are required to have a first-class appearance. Although metal parts should never be permanently embedded within the cover depth from the surface of the concrete, internal ties can be used in ways which will not detract from the appearance. For instance, if made coincident with certain types of surface features (eg vertical grooves formed to break up large areas or features which create shadow effects) the holes are practically indiscernible and an economical design of formwork ensues. The designer is urged to be flexible in his requirements for surface features bearing such facts in mind. For Class F3 and F4 finishes, it is recommended that trial panels should be made. Class F5 finish is primarily intended for precast pretensioned beams. The position of the exposed surfaces in the finished structure should be taken into account in determining the extent of making good. In cases where beams are of the same design it is possible, within practical limits, to minimise the extent of making good by selecting beams

with the best surface finish for positions of maximum exposure.

There have been some difficulties over what constitutes an acceptable finish in precast prestressed beams. Therefore before an order is placed it is advisable to inspect typical beams from a beam manufacturer's works before deciding whether a finish is required which is different from that normally produced.

- (ii) (05/01) Class U2 finish should normally be specified for exposed concrete; Class U3 being reserved for positions where the surface is required to be especially smooth for functional or aesthetic reasons; Class U4 finish is to be used for bridge decks that are to receive waterproofing systems; Class U5 finish is reserved for footbridge surfaces that are to receive either separate or combined systems, or coatings of waterproofing and surfacing materials. The method adopted for finishing a surface which is to receive deck waterproofing should be such that a layer of laitance is not left on the surface nor the coarse aggregate exposed.
- (iii) Other classes of finish should be fully specified and scheduled in Appendix 17/3 and should, if possible, be related to samples that are readily available for comparison. Included under this heading is any finish that requires the coarse aggregate to be permanently exposed, the use of special forms or linings, the use of a different concrete mix near the surface, grinding, bush-hammering or other treatment.

### Protection

5 High quality surface finishes are susceptible to subsequent damage, and special protection may have to be provided in vulnerable areas.

## NG 1709 Concrete - Surface Impregnation

### General

1 (05/01) Impregnation is carried out by spraying concrete surfaces with a hydrophobising material that penetrates the concrete and reacts with the silicates and moisture present. This produces a water repellent but vapour permeable layer that inhibits the ingress of water and/or chloride and sulfate ions. Effectiveness of this layer is determined by the quality of the hydrophobisation and the strength and permanence of the bond between the silane molecule and the concrete

substrate. The depth of penetration will vary depending on concrete quality and moisture content. Impregnation is known to be effective for at least 15 years provided it has been applied correctly. Longer service lives are anticipated. However, it is considered advisable until further experience is gained to assume that reapplication will be necessary after about 20 years.

2 (05/01) Because of the wide variety of structural types and span arrangements, etc. all parts of a structure are not equally at risk from attack. Generally the risk depends upon the degree of exposure to water and salts which in turn will depend on the geometry, design and location of individual members. It is highly desirable to treat all exposed reinforced and prestressed concrete surfaces subjected to spray and/or possible leakage from deck joints. The following is intended as a guide when completing Appendix 17/2:

- (i) piers, columns, crossheads and abutments subjected to spray;
- (ii) piers, columns, crossheads and abutments with a deck joint above but with no provision for positive drainage. The tops of these members should also be treated where possible;
- (iii) bearing shelves, ballast walls and deck ends with a deck joint above, where possible;
- (iv) structures in marine environments and columns and soffits over brackish water. A marine environment is usually experienced within 1 km of the coast or tidal waters unless there are special local conditions.
- (v) where possible, concrete parapets and parapet plinths (all inclinations) and those areas not protected with deck waterproofing;
- (vi) deck beams and soffits;
- (vii) wing walls within 8 metres of the edge of the carriageway;
- (viii) retaining walls within 8 metres of the edge of the carriageway;
- (ix) 'M' beams (webs and tops of bottom flanges should be treated before erection).

### Material

3 (i) (05/01) Silane is a toxic material and is an irritant to human tissue. Containers must be retained in a safe and secure facility and quantities used must be carefully monitored. Access for sampling of opened containers and at the spraying equipment must be provided for the Overseeing Organisation.



- (ii) (05/01) Silane hydrolyses with moisture in the atmosphere. The contents of any opened containers should be used in accordance with sub-Clause 8 of this Clause within 48 hours or discarded
- (iii) (05/01) Silane can be contaminated with substances such as paraffin or white spirit without any visual indications. It is important to test for such contamination by measuring the refractive index of the silane and taking the necessary actions as indicated in sub-Clause 1709.2.

#### Spraying Equipment (05/01)

4 The type of nozzle used and spraying distance should be in accordance with the manufacturer's instructions.

#### (05/01) Protective Measures

- 5 (i) Silane may have deleterious effects that need to be controlled during the application of the material. Prior to application, protective measures must be implemented to prevent contamination of watercourses and damage to humans, animals, vegetation and vehicles.
- (ii) Impregnation over or adjacent to watercourses will require protective sheeting or complete encapsulation beneath the structure to be impregnated.
- (iii) Impregnation on structures over or adjacent to roads will require protective sheeting or complete encapsulation. Consideration should also be given to the introduction of appropriate traffic management and safety measures.
- (iv) Vegetation that could be subject to spray, needs to be covered or otherwise protected, and the protective covering must be maintained in position and in good condition.
- (v) Silane has a softening effect when it comes into contact with elastomeric bearings, painted steel surfaces, bituminous materials and joint sealants, and these items should be protected during application. The protective measures must be maintained in position and in good condition. On completion of the impregnation process the masking materials should be removed and disposed of in accordance with sub-Clause 8 of this Clause.

#### (05/01) Surface Condition

- 6 (i) It should be ensured that curing membranes and release agents, where they have been used, have fully degraded before impregnation is carried out. This is particularly important to check when silane is to be applied less than a month after the concrete was placed.
- (ii) Water jetting or steam cleaning should not in general be used to remove contamination, solid deposits or curing membranes. In exceptional circumstances, where there is substantial contamination, these methods may be used with care, subject to a satisfactory trial being undertaken. However, impregnation should not commence for a minimum of 48 hrs from completion of the cleaning works, and remains subject to the other application and surface condition requirements, particularly the need for a period of surface dryness of the concrete substrate for a period of 24 hours in advance of the impregnation operation.
- (iii) Silane should not be applied until the concrete surface has been dry for 24 hours because absorption of silane will be restricted if damp, reducing its effectiveness. Artificial drying of the concrete surface is not permitted, as this may lead to increased moisture at the surface by capillary action from within the concrete, when the drying equipment is removed.

#### (05/01) Application

- 7 (i) Depending on climatic conditions, it may be necessary to protect surfaces to be treated to ensure that they are surface dry before impregnation.
- (ii) The required coverage of each coat at 300 ml/m<sup>2</sup> must be regularly monitored by determining the quantities of silane material used on particular areas of each structure. Achieving the required rate may result in some loss of material, by run down and evaporation. Application of silane can be judged by a characteristic 'wet look' to the concrete.
- (iii) It is important to apply the silane before the concrete receives its first exposure to salts, subject to the prior degradation of any curing membranes, because a substantial amount of contaminants can enter the concrete by capillary adsorption during this initial

exposure. This may be particularly important in a marine environment.

(05/01) **Disposal**

8 Given the toxic nature of silane, the contents of all containers that have been opened for more than 48 hrs, contaminated materials, sheeting etc, must be disposed of appropriately at an approved disposal facility. Quantities of materials must be monitored on site and materials kept in safe and secure facilities.

(05/01) **Materials Testing**

- 9 (i) It is essential that volumes of impregnation material delivered to site, used on site and for disposal, are accurately monitored.
- (ii) Samples of impregnation material (refer to sub-Clause 1709. 2(vi)) should be tested to confirm compliance with the requirements of sub-Clause 1709. 2(ii).

## NG 1710 Concrete - Construction General

### Construction Joints

1 (05/01) The number of construction joints should be kept as few as possible consistent with reasonable precautions against shrinkage and early thermal movement. Concreting should be carried out continuously up to construction joints.

Where it is necessary to introduce construction joints, careful consideration should be given to their exact location, which should be shown either on the Drawings or determined by the Contractor in accordance with the specified criteria. Construction joints should be at right angles to the general direction of the member and should take due account of shear and other stresses.

The use of retarding agents painted onto formwork should be discouraged because they tend to migrate into the concrete under the action of vibration.

When open mesh permanent formwork is proposed, its suitability should be supported by sufficient information about its stiffness, strength, method of use and performance.

Concrete should not be allowed to run to a feather edge and vertical joints should be formed against a stop end. The top surface of a layer of concrete should be level and reasonably flat unless design requirements are otherwise. Joint lines should be so arranged that they coincide with features of the finished work.

If a kicker (ie a starter stub) is used, it should be at least 70 mm high and carefully constructed. Where possible,

the formwork should be designed to facilitate the preparation of the joint surface, as the optimum time for treatment is usually a few hours after placing.

Particular care should be taken in the placing of the new concrete close to the joint. This concrete should be particularly well compacted.

### Formwork

- 2 (i) Design and construction. It should be ensured that all permanent or temporary formwork, including supports, is adequate for the proper construction of the Works.

Before any formwork is constructed, the Contractor should prepare detail drawings, including details of external vibrators where proposed and the depth of lifts to be concreted where appropriate. The drawings should be supported by calculations which show the adequacy of the proposals.

Requirements for permanent formwork, for either internal or external use, should be described in Appendix 17/4; due regard being given to the conditions to which it is likely to be exposed and to its function in the structure. The material selected for external use must be durable, particularly at exposed edges or joints.

- (ii) Projecting reinforcement. Special care should be taken when formwork is struck to avoid the risk of breaking off the edge of concrete adjacent to any projecting reinforcement.

### Transporting, Placing and Compacting

3 Concrete should be transported from the mixer to the formwork as rapidly as practicable by methods that will prevent the segregation or loss of any of the ingredients and maintain the required workability. It should be deposited as near as practicable to its final position to avoid rehandling.

All placing and compacting should be carried out under the direct supervision of a competent member of the Contractor's (or manufacturer's) staff. Concrete should normally be placed and compacted soon after mixing, but short delays in placing may be permitted provided that the concrete can still be placed and effectively compacted without the addition of further water.

A cohesive concrete mix that does not segregate may be allowed to fall freely provided that special care is taken to avoid displacement of reinforcement or movement of formwork, and damage to faces of formwork. In massive sections it is necessary to consider the effect of

lift height on the temperature rise due to the heat of hydration.

Concrete should be thoroughly compacted by vibration, pressure, shock or other means during the operation of placing to produce a dense mass having the required surface finish when the formwork is removed.

Whenever vibration has to be applied externally, the design of formwork and disposition of vibrators should receive special consideration to ensure efficient compaction and to avoid surface blemishes.

The mix should be such that there will not be excess water on the top surface on completion of compaction. It may be necessary to reduce the water content of batches at the top of deep lifts to compensate for water gain from the lower levels, but this can be avoided by designing the mix, checking with preliminary trials and accurately controlling the mix proportions throughout the work.

Spillages of concrete onto other parts of the permanent structure, eg. structural steelwork, should be removed immediately they occur to avoid damage to finishes. When air entrained concrete is used, reference should also be made to NG 1703.3(ii).

### Striking of Formwork

- 4 (i) General. The time at which formwork is struck is influenced by the following factors:
- (a) concrete strength;
  - (b) stresses in the concrete at any stage in the construction period, which in the case of precast units includes the stresses induced by disturbance at the casting position and subsequent handling;
  - (c) curing (see NG 1710.5);
  - (d) subsequent surface treatment requirements;
  - (e) presence of re-entrant angles requiring formwork to be removed as soon as possible after concrete has set to avoid shrinkage cracks;
  - (f) requirements of any deflection profile.

The formwork should be removed slowly, as the sudden removal of wedges is equivalent to a shock load on the partly hardened concrete.

- (ii) (05/02) Striking period for cast in situ concrete.

Field conditions for control cubes may be simulated by temperature-matching curing or

other methods. In the absence of control cubes, reference should be made to the specialist literature, eg "Formwork Striking Times-Methods of Assessment" prepared by CIRIA (Report No 67) for appropriate guidance.

The periods given in Table 17/12 of the Specification are not intended to apply where accelerated curing or slip forms are used. Where it is not practicable to ascertain the surface temperature of concrete, air temperatures may be used though these are less precise. In cold weather the period should be increased according to the reduced maturity. For example, for soffit formwork it would be appropriate to increase the value by half a day for each day on which the concrete temperature was between 2°C and 7°C, and by a whole day for each day on which the concrete temperature was below 2°C.

When formwork to vertical surfaces such as beam sides, walls and columns is removed in less than 12 hours, care should be exercised to avoid damage to the concrete, especially to arises and features. The provision of suitable curing methods should immediately follow the removal of the vertical formwork at such early ages, and the concrete should be protected from low or high temperatures by means of suitable insulation (see NG 1710.5).

### Curing

- 5 (i) Curing Methods. The method of curing and its duration should be such that the concrete will have satisfactory durability and strength and the member will suffer a minimum of distortion, be free from excessive efflorescence and undue cracking. To achieve these objectives it may be necessary to insulate the concrete so that it is maintained at a suitable temperature, or so that the rates of evaporation of water from the surfaces are kept to appropriate values, or both. Different curing or drying treatments are appropriate to different members and products. Where necessary, special care should be taken to ensure that similar components are cured as far as possible under the same conditions.

Curing usually consists of maintaining the formwork in place and covering the concrete with a material such as polythene sheet or a

curing compound or with an absorbent material that is kept damp for a period of time.

Where formwork is struck before curing is complete some other form of protection should be used.

Where structural members are of considerable depth or bulk or have an unusually high proportion of cement or are precast units subjected to special or accelerated curing methods, the method of curing should be specified in detail. Some special cases are cited as examples in NG 1710.5(iii).

The higher the rate of development of strength in concrete, the greater the need to prevent excessive differences in temperature within the member and too rapid a loss of moisture from the surface. Alternate wetting and drying should be avoided, especially in the form of cold water applied to hot concrete surfaces. In order to avoid surface cracking, cold water should not be applied to relatively massive members immediately after striking the formwork while the concrete is still hot.

- (ii) Accelerated curing. Accelerated curing (which includes steam curing) consists of curing the concrete in an artificially controlled environment, in which the humidity and the rate of temperature rise and fall are controlled, to speed up the rate of increase in strength.

- (iii) Additional Considerations.

The principal reasons and recommendations for curing concrete are given in (i) and (ii) above. The following parts of this sub-Clause are intended to amplify the factors that should be considered. The recommendations are based on the assumption that the concrete temperature during the curing period will not fall below 2°C. Particular precautions to be taken when concreting at low air temperatures are given in NG 1710.6.

- (a) Strength of concrete. The effect of admixtures on curing should be considered. The higher the rate of development of strength of the concrete (and hence of heat of hydration of the cement), the more care should be taken during the early period after casting to prevent excessive differences in

temperature within the concrete and excessive loss of moisture from the pour.

The rate of gain of strength is also increased if the temperature of the concrete is raised. An approximate guide to the development of strength at different temperatures can be obtained by using the concept of 'maturity', which may be defined as the area under a curve of the concrete temperature (in degrees Celsius) plotted against time (in hours) calculated from a basis of -10°C. Curing by means of damp absorbent materials is likely to cause a lowering of the temperature of the concrete as a result of the evaporation from the material, and in some circumstances the effect can be significant.

The rate of development of strength diminishes as the concrete dries out; hence excessive evaporation of water from all surfaces may need to be prevented.

- (b) Distortion and cracking. The concrete should be cured so that internal stresses within the member, whether due to differences in temperature or differences in moisture content within the concrete, are not sufficient to cause distortion or cracking. The disposition of reinforcement will affect the restraint to the strains, and hence it will have an effect on any distortion and cracking.

In assessing the likely temperature variation within the concrete, the following factors apply:

- rate of heat evolution (related to rate of development of strength);
- size and shape of member;
- different insulation values of curing media (eg wooden moulds or water spray);
- external temperature.

For example, surface cracking may occur as a result of variation in temperatures due to applying a cold water spray to a relatively massive member immediately after stripping the moulds while the concrete is still hot.

In assessing the likely variation in moisture content within the concrete,

the rate of evaporation from unprotected concrete will be higher with atmospheric conditions encouraging evaporation (eg low relative humidity, high wind speed, concrete surface hotter than the air), especially if the rate of migration of water through the concrete is greater than the rate of evaporation from the surface, eg for:

- members of high surface/volume ratio;
- concrete at early age or lower grade of concrete.

For example, cracking may occur due to varying shrinkage in members with sudden changes in section that affect the surface/volume ratio appreciably; especially if the more massive section is reinforced and the more slender section is not.

Further information can be obtained from CIRIA Report No 91, "Early-age Thermal Crack Control in Concrete".

If the shrinkage of units after they are built into the structure is likely to lead to undesirable cracking at the ends of the unit, curing aimed at preventing the loss of water from the unit should be continued no longer than is necessary to obtain the desired durability and strength; thereafter the concrete should be given the maximum opportunity to dry out consistent with the limitation of the variation in moisture content as already outlined.

- (c) (05/02) Durability and appearance. As deterioration is most likely to occur as a result of the concrete providing inadequate protection for the reinforcement, or because of frost attacking the surface concrete, all vulnerable surfaces of concrete should be protected against excessive loss of water by evaporation that would result in a weak, porous surface layer.

Where it is important to prevent the formation of efflorescence, especially in cold weather, the atmosphere adjacent to the surface of the concrete should be maintained at a constant relative humidity approaching 100% for the time given in Table 17/13 of the Specification. Concrete should be

protected from wetting and drying cycles.

- (iv) Curing liquids, compounds and membranes. Before curing liquids, compounds and membranes are accepted for use on surfaces on which waterproofing systems are to be laid they should be shown to be completely removable by natural or mechanical means.

It should be noted that proprietary liquid curing membranes may take a long time to disintegrate and may affect the appearance of permanently visible surfaces as well as the bond of any waterproofing layer.

Only film type membranes that fully degrade by exposure to ultra-violet light should be used where concrete surface impregnation is specified, as other curing liquids, compounds or membranes may leave residues which prevent satisfactory application of the treatment. Sufficient interval should be allowed for the film to fully decompose before impregnation commences (see NG 1709.5). To achieve optimum breakdown of the membrane the manufacturer's recommendations for prior wetting or dampening of the concrete surfaces and the rate of application of the membrane material should be closely followed.

### Cold Weather Work

- 6 (i) General. Before placing concrete, the formwork, reinforcement, prestressing steel and any surface with which the fresh concrete will be in contact should preferably be at a temperature close to that of the freshly placed concrete. Special care should be taken where small quantities of fresh concrete are placed in contact with larger quantities of previously cast concrete at a lower temperature. Any concrete damaged by frost should be removed from the work.

Concrete temperatures should be measured at the surface at the most unfavourable position.

- (ii) Concrete Temperature

The raising of the temperature of the concrete may be achieved in a number of ways including the following:

- (a) By heating the mixing water and aggregate. If the water is heated above 60°C, it is advisable to mix the water

with the aggregate before adding the cement.

- (b) By increasing the cement content of the mix or by using a more rapid hardening cement.
- (c) By covering the top face of slabs and beams with adequate insulating material.
- (d) By providing wind breaks to protect newly placed concrete from cold winds.
- (e) By using a heated enclosure, completely surrounding the freshly placed concrete or using heated formwork panels. In either event care should be taken to prevent excessive evaporation of water from the concrete.

Formwork should be left in place as long as possible to provide thermal insulation; timber formwork provides better insulation than steel. Further guidance on this subject can be obtained from the Cement and Concrete Association Publication No. 45.007 "Winter Concreting".

### Hot Weather Work

7 In hot weather, the incidence of cracking and loss of workability may be reduced if measures are taken to cool the constituent materials. Aggregates can be kept cool by protecting them from direct sunlight and by spraying with water, making due allowance for the moisture content of the mix. Water pipes particularly if long should preferably be shaded and if possible insulated.

### Surface Preparation of Precast Concrete Units

8 (05/01) Laitance is the dusty milky cement compound which can be removed after the concrete has hardened using a stiff brush.

### Handling and Erection of Precast Concrete Units

- 9 (i) **Manufacture off the Site.** The designer should show on the Drawings the type of preparation of the surfaces of concrete members which will subsequently receive in situ concrete.

Supervision of workmanship and materials for factory-made concrete units is as important as for Site work and is most satisfactorily carried out by a resident inspector or by making frequent visits during manufacture.

To monitor control during production, test results should be readily available. This should help to encourage careful manufacture. Where exceptional circumstances prevent proper supervision being exercised, visual inspection and measurement of the completed units can determine some of the important properties. Reference should also be made to NG 1727. To benefit from manufacturer's normal practice, it is recommended that for factory-made pretensioned beams, the designer should be prepared to accept alternative types and positions of tendons. Where the size and position of the tendons is shown on the Drawings, the words "or equivalent" should be added and the force before transfer and its eccentricity should be given. The designer should ensure that the losses from the type of tendons proposed are no greater than those taken into account in the design.

- (ii) **Storage.** Indelible identity, location and orientation marks should be put on the member end where necessary. The designer should in all cases specify the points of support during storage, and these should be chosen to prevent unacceptable permanent distortion and lack of fit of the units. In order to minimise the stresses induced, supporting arrangements that permit only small settlements are to be preferred.

The accumulation of trapped water and rubbish in the units should be prevented. The freezing of trapped water can cause severe damage.

Where necessary, precautions should be taken to avoid rust stains from projecting reinforcement and to minimise efflorescence.

- (iii) **Handling and transport.** Precast units should resist, without permanent damage, all stresses induced by handling and transport. The minimum age for handling and transport should be related to the concrete strength, the type of unit and other relevant factors.

The position of lifting and supporting points, the method of lifting, the type of equipment, the minimum age for handling, and transport to be used should be as specified by the designer.

Care should be taken to ensure that lifting details are practicable and can be used safely, and that no damage results from the lifting equipment.

During transport the following additional factors require consideration:

- (a) Distortion of the transporting vehicles.
  - (b) Centrifugal force due to cornering.
  - (c) Oscillation. A slim member may flex vertically or horizontally sufficiently to cause damage.
  - (d) The possibility of damage due to chafing.
- (iv) Assembly and erection. Where the method of assembly and erection is part of the design, it should be stated in Appendix 17/4.

In order to ensure compliance with sub-Clause 1710.8(iv)(a) of the Specification, it may be advisable to have the camber of precast beams measured at the factory so that they can be placed in the correct order.

The object of preventing lateral movement of precast beams in composite slab bridges is to prevent differential movement between beams, which may occur if the concrete is placed in longitudinal strips. This is particularly important when the beams are supported on flexible bearings.

- (v) Forming structural connections. The precast units should be inspected to ensure that the design requirements of the structural connection can be met.

The precast units should be free from irregularities which may cause damaging stress concentrations. When reliance is placed on bond between the precast and in situ concretes, the contact surface of the precast unit should have been suitably prepared. If frictional resistance is assumed to be developed at a bearing, the construction should be such that this assumption can be realised. Particular care should be given to checking the accurate location of reinforcement and any structural steel sections in the ends of precast members, and to introducing any additional reinforcement needed to complete the connection.

- (a) Concrete or mortar packing. When joints between units, particularly the horizontal joints between successive vertical lifts, are load-bearing and are to be packed with mortar or concrete, tests should be carried out to prove that the material is suitable for the purpose and that the proposed method of filling

results in a solid joint (for bedding mortar see Clause 2601).

- (b) (05/02) Other packing materials. Where epoxy resin bonding agents for segmental deck construction are to be used the designer should prepare additional specification requirements based on the manufacturer's recommendations. Reference should also be made to Federation Internationale de la Precontrainte (FIP) publication FIP/9/2, available from the British Cement Association.

The composition and water/cement ratio of the in situ concrete or mortar used in any connection should be as specified.

Care should be taken to ensure that the in situ material is thoroughly compacted.

The manufacturer's recommendations as to the application and methods should be strictly followed.

Careful consideration should be given to the proposed methods for removing levelling devices such as nuts and wedges.

- (vi) Protection. The degree and extent of the protection to be provided should be sufficient for the surface finish and profile being protected, bearing in mind its position and importance. This is particularly important in the case of permanently exposed concrete surfaces, especially arrises and decorative features. The protection can be provided by timber strips, hessian, etc, but should not be such as will damage, mark or otherwise disfigure the concrete.

### Measurement of Precast Concrete

**10** Units may be measured at any convenient time but not less than 7 days after casting, provided that the alternative time proposed by the Contractor is supported by calculations to demonstrate the dimensions predicted for  $28 \pm 2$  days.

### NG 1711 (05/01) Concrete - Grouting and Duct Systems for Post-tensioned Tendons.

#### General

**1** The Specification allows for the Overseeing Organisation to call for full-scale trials to be carried out to demonstrate that the grouting will provide adequate protection to the tendons. This requirement should be

specified in Appendix 17/6 and fully detailed on a Contract drawing, including trial beam size, concrete grade, cover to reinforcement and tendons, reinforcement and tendon details, together with requirements for testing and investigation. The designer should recognise that the purpose of the trial is to test the Contractor's systems and methods proposed for the permanent works and should incorporate any particular requirements pertaining to the construction sequence and duct configurations. Requirements for subsequent disposal of the trial beam should be specified.

The trials should be carried out well in advance of the planned need for use of post-tensioning in the permanent works (56 days is the default period in the Specification). In particular, any proposals for untried systems should be given due time for acceptance.

Grouting techniques such as vacuum grouting and post-injection re-grouting (as carried out in Germany) are available from some suppliers and can be considered either to be demonstrated as suitable in trials or for remedial works as appropriate.

### Grout Material

**2** Composition of the grout is classified as common or special (see sub-Clause 1711.2). The designer should specify in Appendix 17/6 the grout type required. Performance of the grout will in all cases be assured by suitability trials, irrespective of whether full-scale grouting trials have been specified.

Where bagged cement is used the Overseeing Organisation should be aware that variations in age, chemical composition, fineness and temperature can have significant effects on the performance of the grout. Additionally, it should be noted that the weight of bagged cement is permitted under British Standards to vary by up to 6% from the nominal weight which could also significantly affect performance of the grout.

### Ducting

**3** Sub-Clause 1711.3 requires the ducting to form an air and water resistant protective barrier as an additional defence against corrosive contaminants, and polyethylene or polypropylene are suggested as suitable materials although other materials may be used. This follows the philosophy of multi-layer corrosion protection. The intention is that if the duct is inadvertently not completely filled with grout the risk that this poses to the tendons may be significantly reduced as the protective ducting should maintain a corrosion-free environment.

Debate continues over the necessary minimum wall thickness of ducting, given in the Specification as 2 mm (manufactured) and 1.5 mm after tensioning, and over

the air pressure test requirements. The purpose of air testing is to demonstrate, first, that the system provides an adequate degree of resistance to the ingress of contaminants and, second, that the system is correctly assembled and has no significant leaks. Some systems will not withstand the 0.1 N/mm<sup>2</sup> pressure previously specified for the test, yet are completely leakproof at half this pressure. The pressure testing requirements have been amended to introduce reference to compliance testing before installation (see also TR 47, Durable Bonded Post-Tensioned Concrete Bridges, Section 5.3) and duct assembly verification testing. It is expected that all currently available systems can pass the latter test but designers should seek the prestressing system supplier's guidance before completing Appendix 17/6, particularly with respect to compliance testing for the more onerous criteria suggested in TR 47 Section 5.3.

The minimum wall thickness specified is not currently available for all duct diameters and a relaxation of this may be necessary for certain ducts. It is recommended that supplier's guidance is sought on availability and compliance with this requirement before completing Appendix 17/6.

There are circumstances where the requirement for a sealed ducting system will be difficult eg in segmental construction. The designer should consider the options. Sealing of ducts at joints in segmental construction is an issue which remains to be satisfactorily resolved.

Minimum wall thickness of the ducting after tensioning should be considered by the designer and appropriate requirements specified in Appendix 17/6, taking account of minimum radii of curvature of the tendons which will tend to bite into the duct wall. Type and spacing of duct supports also need careful attention to avoid this. Manufacturers' and suppliers' data should be referred to.

The internal diameter of vents should be as large as possible but designers should bear in mind the sizes included within available systems. The vents, connections and taps should be sufficiently robust to withstand full grouting pressure.

For most applications a minimum vent height of 500 mm above the highest point on a duct is recommended to help entrapped air and water to escape. For some configurations of tendons this will not be appropriate and the designer should specify an alternative in Appendix 17/6.

Some designers and some applications may require closer vent spacing than the 15 m in the general Specification. Any other requirement should be given in the Appendix.



## Grouting Equipment

4 The mixing equipment should be of a type capable of producing a homogeneous grout by means of high local turbulence while imparting only a slow motion to the body of the grout.

## Injecting Grout

5 The volume of the spaces to be filled by the injected grout should be compared with the quantity of grout injected.

## Grouting During Cold Weather

6 The grout materials may be warmed within the limits recommended for concrete (see NG 1710.6).

## Testing

7 The requirement for bond length is given as 40 diameters of the duct. If the designer wishes to give an alternative, this should be specified in Appendix 17/6.

The mandatory Duct Assembly Verification Test included in the Specification is intended to demonstrate that the system has been correctly assembled. If the system fails to meet the criteria required by the Test, it should be dismantled, any damaged items replaced, and the system reassembled and re-tested. If it still fails to comply, sealing of joints with the addition of a suitable sealant may improve matters. Acceptance would then be subject to the Overseeing Organisation's decision on the results of re-testing.

Section 5.3 (TR 47) describes two additional tests to measure the degree of seal provided by the duct system, which the designer may wish to consider adopting in appropriate circumstances. Both methods require further experience and development before adoption as a specification requirement.

The test described in Section 5.3.1 (TR 47), the Pre-grouting Pressure Test, will measure the seal achieved with the duct in its final condition. The leakage flow rate should be recorded at the test pressure, and results reported to the Overseeing Organisation for record purposes. Whilst the pressure is applied to the duct, potential external sources of leakage should be checked by soap solution, or other non-destructive tests undertaken to detect the source of significant leakage. Measures should be taken to eliminate or reduce the consequences of identified leakage, with the agreement of the Overseeing Organisation.. Such measures should be limited to sealing of end caps, crack sealing, additional waterproofing, or any special grouting measures.

The test described in Section 5.3.2 (TR 47) is a method of gaining type-approval for a duct system to qualify as a sealed system, and provides the data from which site tests may be more accurately judged.

The fluidity of the grout during the injection period should be sufficiently high for it to be pumped effectively and adequately to fill the duct, but sufficiently low to expel the air and any water in the duct.

The bleeding of grout should be sufficiently low to prevent excessive segregation and settlement of the grout materials.

The Overseeing Organisation should adopt a pragmatic approach to the size of acceptable voids in ducts. The 5% limit given in sub-Clause 1711.1 would normally be acceptable at a crest in the duct where the steel tendons are embedded in grout in the lower part of the duct and the vents are properly filled and sealed, and the surface is waterproofed.

The requirements for testing (see Table 17/15) should be included in Appendix 17/6.

## Admixtures

8 Expanding grout admixtures are supplied as powders which expand to ensure that there is no overall decrease in the volume of grout at the end of the hardening period.

Non-expanding grout admixtures are supplied in liquid or powder form.

Both types of grout admixture may also permit a reduction in water/cement ratio, improve fluidity, reduce bleeding and retard the set of the grout.

## NG 1712 (05/01) Reinforcement - Materials

### Bond Classification

1 The designer should state in Appendix 17/4 the type of deformed bar required in accordance with BS 8666.

### (05/02) Stainless Steel Reinforcement

2 Advice on stainless steel reinforcement is given in BA 84 (DMRB 1.3). Since there are a multiplicity of grades of stainless steel, it is essential that supplied steel is clearly designated with its strength and chemical grade, and that care is taken to ensure that the correct materials are utilised.

### **NG 1713 (05/02) Carbon Steel Reinforcement and Stainless Steel Reinforcement - Bar Schedule Dimensions - Cutting and Bending**

1 (05/01) Bending of reinforcement should not be carried out when the temperature of the steel is below 5°C. If necessary, reinforcement may be warmed to a temperature not exceeding 100°C.

Where it is necessary to bend reinforcement projecting from concrete, the radius of the bend should be not less than that specified in BS 8666, and there should be a clear distance of 4d between the concrete face and the start of the bend. Embedded couplers should be used wherever practicable to avoid damage to concrete and reinforcement.

2 (05/01) Where the Contractor or precast manufacturer opts to cut and bend reinforcement on the Site, or in the precasting works respectively, even though the CARES fabricators offer this service, it should be ensured that any fabricated reinforcement not covered by a third party certificated product certification scheme such as CARES is assessed by acceptance tests carried out by an independent testing laboratory as specified in BS 8666.

### **NG 1714 Reinforcement - Fixing**

1 (05/01) Cover blocks and spacers should be of such materials and designs that they will be durable, will not lead to corrosion of the reinforcement, and will not cause spalling of the concrete cover.

Cover and spacer blocks made from cement, sand and fine aggregate should match the mix proportions of the surrounding concrete as far as is practicable with a view to being comparable in strength, durability and appearance. The Concrete Society Report CS 101 "SPACERS" provides standardised methods of achieving the specified nominal cover and gives standard performance requirements and methods of testing spacers and chairs.

Non-structural connections for the positioning of reinforcement should be made with stainless steel wire or tying devices or by welding (see NG 1717). Care should be taken to ensure that projecting ends of ties or clips do not encroach into the concrete cover.

The cover and position of reinforcement should be checked before and during concreting; particular attention being paid to the position of top reinforcement in cantilever sections. The support of reinforcement to achieve the correct location, cover and spacing is the Contractor's responsibility and supports should not be shown on the Drawings and Bar Schedules.

The concrete cover to reinforcement should be confirmed as soon as possible after the removal of formwork, by the use of non-destructive methods of testing (see NG 1727.2(ii)(d)). A record of this survey should be retained for inclusion in the as-built drawings.

### **NG 1715 Reinforcement - Surface Condition**

1 (05/01) Normal handling prior to embedment in the concrete is usually sufficient for the removal of loose rust and scale from reinforcement; otherwise wire-brushing or sand-blasting should be used. The sand used for blasting should comply with BS 1199 and BS 1200.

### **NG 1716 Reinforcement - Laps and Joints**

#### **General Requirements**

1 Where continuity of reinforcement is required through the connection, the jointing method used should be such that the assumptions made in analysing the structure and critical sections are realised. The following methods may be used to achieve continuity of reinforcement:

- (i) lapping bars;
- (ii) mechanical joints;
- (iii) threaded reinforcing bars;
- (iv) welding (see NG 1717).

Such connections should occur, where possible, away from points of high stress and should be staggered. The use of any other jointing method not listed should be confirmed by test evidence.

#### **Lapping of Bars**

2 Where straight bars passing through the joint are lapped, the requirements of BS 5400 : Part 4 apply. When reinforcement is grouted into a pocket or recess, an adequate shear key should be provided on the inside of the pocket.

Where continuity over a support is achieved by having dowel bars passing through overlapping loops of reinforcement, which project from each supported member, the bearing stresses inside the loops should be in accordance with BS 5400 : Part 4.

#### **Jointing of Bars**

3 A number of systems are available for jointing reinforcing bars, which are capable of transmitting the

tensile and compressive forces in the bar; these are as follows:

- (i) swaged couplers;
- (ii) tapered threaded bars and couplers;
- (iii) upset bar ends with parallel threads and couplers;
- (iv) couplers fixed to the bars with studs for transmitting compressive forces only;
- (v) (05/02) sleeves with tapered closers that align the square sawn ends of bars for transmitting compressive forces only.

Mechanical Joints should have a current British Board of Agrément Roads and Bridges or CARES Certificates.

Mechanical joints for stainless steel reinforcement should have equivalent durability to the reinforcement itself. They require specific approval from the Overseeing Organisation in respect of the technical design requirements.

## NG 1717 Reinforcement - Welding

### General

**1** (05/01) Welding should be avoided whenever possible. Very significant loss in fatigue strength of reinforcement can occur as a result of welding. Location welds (tack welds used for locating bars) pose a particular fatigue risk (see BS 5400 : Part 10) and any welding to shear stirrups requires careful assessment.

Welding may only be undertaken where suitable safeguards, supervision and techniques are to be employed. Where it is acceptable in the design and to BS 5400 : Part 4 and Part 10 it should be checked that where cyclic loading occurs, the Class of weld given in Table 17 of BS 5400 : Part 10 has been achieved.

Where, notwithstanding the above, welding is to be used, and the fatigue effects of the welds have been taken into account in the design it should if possible be carried out under controlled conditions in a factory or workshop. The competence of the operators should be demonstrated prior to, and periodically during, welding operations.

In such circumstances welding may be considered for:

- (i) Fixing in position, eg. by welding between crossing or lapping reinforcement or between bars and other steel members. Metal-arc welding or electric-resistance welding may be used on suitable steels.
- (ii) Structural welds involving transfer of load

between reinforcement or between bars and other steel members. Butt welds may be carried out by flash butt welding or metal-arc welding.

The manual metal-arc process is used on Site or in fabrication shops for making joints of every configuration. In particular it is the only process available for making tee joints between bars and anchorage plates and lapped joints between bars. It is emphasized that operators should be trained and possess sufficient skill for producing good welded joints. The flash butt welding process is restricted to fabrication shops where it can produce sound butt welds more rapidly than manual metal-arc welding. The resistance welding process for cross bar joints can be used on Site or in fabrication shops, though for work on Site it is more usual to use manual metal-arc welding. Further guidance on metal-arc welding of reinforcing bars is given in BS 7123.

**2** Flash butt welding is carried out by clamping the reinforcing steel bars in water-cooled copper shoes which introduce a large current to the bars. The bar faces are moved slowly towards each other and, when in close proximity, arcing or flashing occurs at those parts of the two faces in closest contact. The arcing or flashing results in intense heating of the bars. This flashing period can be extended to further preheat the joint before completing the weld which is performed by forcing the hot faces together, metal being forced from the hot faces during the actual welding stage to form a collar. Advice on the correct combination of flashing, heating, upsetting and annealing should be obtained from the reinforcement manufacturer.

**3** Manual metal-arc welding is a form of fusion welding in which heat for welding is obtained from an arc struck between a consumable stick electrode and the joint faces. The stick electrode consists of a metal core and a flux covering, the flux forming a protective shield for the molten metal in the weld pool, protecting it from atmospheric contamination. In addition the flux includes constituents that can slag off some harmful contaminants that may be present in the joint prior to welding.

**4** Other methods such as resistance welding may be used for forming butt welds. This is a similar operation to flash butt welding, contact of the bar faces creating intense heat due to electrical resistance at the interface. After a predetermined period, sufficient to heat the bar faces into a plastic state, the current is turned off, the bars faces are pressed together under great pressure and a welded joint made, with less material upset than arises in flash butt welding. It is, however, necessary to have cleaner bar faces for resistance butt welding than for flash butt welding.

Resistance welding is rarely used for butt welding of reinforcing steel bars, but resistance spot welding finds wide application for joining wires and bars in cross weld configurations. Large automatic machines with multiple pairs of electrodes are used for simultaneously welding many wires and smaller diameter bars to form mesh. In addition portable guns with single pairs of electrodes are used for tack welding bars of smaller diameter.

Should fabricators wish to use other processes, reference should be made to the reinforcement manufacturer for guidelines in developing satisfactory procedures.

### NG 1718 Prestressing Tendons - Materials

1 The characteristic strengths of prestressing tendons are given in the appropriate British Standards.

### NG 1719 Prestressing Tendons - Handling and Storage

1 (05/01) Protective wrappings for tendons should be chemically neutral, and suitable protection should be provided for the threaded ends of bars.

When prestressing tendons have been stored on Site for a prolonged period, it should be demonstrated by tests that the quality of the prestressing tendons has not been significantly impaired either by corrosion, stress corrosion, loss of cross-sectional area, or by changes in any other mechanical characteristic.

### NG 1720 Prestressing Tendons - Surface Condition

1 (05/01) All prestressing tendons and internal and external surfaces of sheaths or ducts should be free from loose mill scale, loose rust, oil, paint, grease, soap or other lubricants, or other harmful matter at the time of incorporation in the structural member. Slight surface rusting is not necessarily harmful and may improve the bond. It may, however, increase the loss due to friction.

Cleaning of tendons may be carried out by wire brushing or by passing them through a pressure box containing carborundum powder. Solvent solutions should not be used for cleaning.

### NG 1722 Prestressing Tendons - Cutting

1 (05/01) In post-tensioning systems the heating effect on the tendon due to cutting should be kept to a minimum both to avoid damage to the anchorage or

bond of the tendon, and to avoid any undesirable metallurgical effects in the tendon steel within the concrete member. Where tendons between beams on long line prestressing beds are to be cut, the yielding of steel in burning imparts less of a shock load to the beam ends than any cold cutting method and is, therefore, to be preferred.

### NG 1723 Prestressing Tendons - Positioning of Tendons, Sheaths and Duct Formers

1 The method of supporting and fixing the tendons (or the sheaths or duct formers) in position should be such that they will not be displaced by heavy or prolonged vibration, by pressure of the wet concrete, by workmen or by construction traffic. The means of locating prestressing tendons should not unnecessarily increase the friction when they are being tensioned.

Sheaths and extractable cores should retain their correct cross section and profile and should be handled carefully to avoid damage. Extractable cores may be coated with release agent and should not be extracted until the concrete has hardened sufficiently to prevent it being damaged.

Damage can occur during the concreting operation, and if the tendon is to be inserted later, the duct should be dollied during the concreting process to ensure a clear passage for the tendon. Inflatable rubber duct formers are not suitable for this purpose.

Should the profile of any empty duct be in doubt after the concrete has been cast a technique has been developed of drawing a radioactive source through the duct and plotting its path.

### NG 1724 Prestressing Tendons - Tensioning

#### General

1 Tendons may be stressed either by pretensioning or by post-tensioning according to the particular needs of the form of construction. In each system different procedures and types of equipment are used, and these govern the method of tensioning, the form of anchorage and, in post-tensioning, the protection of the tendons.

#### Safety Precautions

2 (05/01) A tendon when tensioned contains a considerable amount of stored energy which, in the event of any failure of tendon, anchorage or jack, may be released violently. All possible precautions should be taken during and after tensioning to safeguard persons from injury, and equipment from damage, that may be caused by the sudden release of this energy. Guidance

on the precautions which should be taken is given in Appendix C to BS 5400 : Part 8.

### Pretensioning

3 The transfer of stress should take place slowly to avoid shock that would adversely affect the transmission length.

### Post-tensioning

- 4 (i) Arrangement of tendons. Tendons, whether in anchorage systems or elsewhere should be so arranged that they do not pass around sharp bends or corners likely to provoke rupture when the tendons are under stress.
- (ii) Anchorage system. The anchorage system in general comprises the anchorage itself and the arrangement of tendons and reinforcement designed to act with the anchorage. The form of anchorage system should facilitate the even distribution of stress in the concrete at the end of the member, and should be capable of maintaining the prestressing force under sustained and fluctuating load and under the effect of shock.

Provision should be made for the protection of the anchorage against corrosion.

- (iii) (05/01) Tensioning procedure. The measured tendon force should be compared with that calculated from the extension, using the Youngs Modulus (E) value for the tendon obtained by measuring the load-extension relationship in a calibrated testing machine with an extensometer of 1 m gauge length. This provides a check on the accuracy of the assumption made for the frictional losses at the design stage; if the difference is significant, corrective action should be taken.

Where a large number of tendons or tendon elements are being tensioned and the full force cannot be achieved in an element because of breakage, slip or blockage of a duct, and if the replacement of that element is not practicable, the designer should consider whether a modification in the stress levels can still comply with the design requirements.

The designer should specify the order of loading and the magnitude of the load for each tendon.

## NG 1725 Prestressing Tendons - Protection and Bond

### General

1 It is essential to protect prestressing tendons from both mechanical damage and corrosion. Protection may also be required against fire damage.

It may also be an important design requirement for the stressed tendon to be bonded to the structure.

### Protection and Bond of Internal Tendons

2 Internal tendons may be protected and bonded to the member by cement grout in accordance with Clause 1711. Alternatively the tendons may be protected by other materials such as bitumen or petroleum-based compounds, epoxy resins, plastics and the like, provided that bond is not important.

### Protection and Bond of External Tendons

3 (05/01) A tendon is considered external when, after stressing and incorporation in the work but before protection, it is outside the concrete section. It does not apply, for example, to a slab comprising a series of precast beams themselves stressed with external tendons and subsequently concreted or grouted in so that the prestressing tendons are finally contained in that filling with adequate cover.

Protection of external prestressing tendons against mechanical damage and corrosion from the atmosphere or other aspects of the environment, should generally be provided by an encasement of dense concrete or dense mortar of adequate thickness. It may also be provided by other materials hard enough and stable enough in the particular environment.

In determining the type and quality of the material to be used for the encasement, full consideration should be given to the differential movement between the structure and the applied protection that arises from changes of load and stress, creep, relaxation, drying shrinkage, humidity and temperature. If the applied protection is dense concrete or mortar and investigations show the possibility of undesirable cracking, then a primary corrosion protection system should be used that will be unimpaired by differential movement.

If it is required that external prestressing tendons be bonded to the structure, this should be achieved by suitable reinforcement of the concrete encasement to the structure.

## NG 1727 Inspection and Testing of Structures and Components

### General

1 This Clause indicates methods for inspecting and, where necessary, testing whole structures, finished parts of a structure, or structural components to ensure that they have the required standards of finish, dimensional accuracy, serviceability and strength. Where inspection or results of other tests (see NG 1727.2) lead to doubt regarding the adequacy of the structure, loading tests may be made following the procedure set out in NG 1727.6.

In this Clause, deflection means the maximum amount of movement under load of the component being tested, relative to a straight line connecting its points of support. The load tests described in this Clause may not be suitable for:

- (i) model testing when used as a basis of design;
- (ii) development testing of prototype structures;
- (iii) testing to prove the adequacy of a structure, owing to change of use or loading.

Where the Contractor or manufacturer uses a quality control method, and maintains records of the entire process of manufacture (subject to these records being certified by a chartered engineer or a person who has a recognised equivalent qualification of another state of the European Economic Area) which show that the products meet the requirements of the Specification, such records may be accepted as confirming that the required quality has been reached. This in no way precludes the designer specifying such tests as he requires.

Testing requirements should be fully described in Appendix 17/4 and scheduled in Appendix 1/5.

### Check Tests on Structural Concrete

- 2 (i) (05/01) General. The testing of concrete specimens to establish whether the concrete used in the structure complies with the Specification as a structural material is described in Clause 1707 and the additional cube tests for special purposes are dealt with in NG 1707.6. The tests described in sub-Clause (ii) below are applicable to hardened concrete in the finished parts of a structure or in precast units. They may be used in routine inspection and for quality control. They are also of use when concrete is found defective from visual inspection and when low cube strengths are obtained when

assessing the strength of the concrete used. Details of procedures are contained in British Standards and advice is provided in the Concrete Bridge Development Group Technical Guide No.2 "Testing and Monitoring the Durability of Concrete Structures" (TG2).

If the results of these check tests show that the quality of the concrete is inadequate or shows other defects, the Contractor may propose that a loading test be made. This should then be carried out in accordance with NG 1727.6.

- (ii) (05/01) Types of check tests
  - (a) Cutting cores. In suitable circumstances the compressive strength of the concrete in the structure may be assessed by drilling and testing cores from the concrete. The procedure used should comply with BS 1881 : Part 201. Such cores may also be cut to investigate the presence of voids in the compacted concrete. Core cutting should, whenever possible, avoid reinforcement.
  - (b) Gamma radiography. Gamma radiography has been used to test concrete up to 450 mm thick for the presence of local voids in the concrete and the efficiency of the grouting of ducts in prestressed members; the presence and location of embedded metal may also be determined. The testing should be carried out in accordance with the recommendations in BS 1881 : Part 205. Further information about gamma radiography testing is contained in Post-tensioned Concrete Bridges published in 1999 by Thomas Telford, specifically Chapter 8. Special precautions are necessary to avoid contamination from the radioactive source.
  - (c) Ultrasonic test. If an ultrasonic apparatus is regularly used by trained personnel and if continuously maintained individual charts are kept that show, for a large number of readings, the relation between the readings and the strength of cubes made from the same batch of concrete, such charts may be used to obtain approximate indications of the strength of the concrete in the structure.

In cases of suspected lack of compaction or low cube strengths, ultrasonic tests carried out on adjacent suspect and acceptable sections of the structure may provide useful comparative data.

- (d) Electromagnetic cover measuring devices. The position of reinforcement or tendons may be verified to depths of about 70 mm by an electromagnetic cover measuring device as described in BS 1881 : Part 204. The position of reinforcement and ducts/tendons may be verified to depths of up to 500mm using an inductive probe as described in TG2.
- (e) Rebound hammer test. If a rebound hammer is regularly used by trained personnel and if continuously maintained individual charts are kept that show, for a large number of readings, the relation between the readings and the strength of cubes made from the same batch of concrete, such charts may be used in conjunction with hammer readings to obtain an approximate indication of the strength of the concrete in a structure or element. An accuracy of  $\pm 3$  N/mm<sup>2</sup> could be expected when used by trained personnel in these circumstances.
- Rebound hammer tests are usually performed on a grid over a defined test area. 12 measurements are obtained around each grid point. Abnormal readings should be discarded and the rebound number determined as the mean of the remaining numbers. (TG2). Readings should not be taken within 25 mm of the edge of concrete members. It may be necessary to distinguish between readings taken on a trowelled face and those taken on a moulded face. When making the test on precast units, special care should be taken to bed them firmly against the impact of the hammer.

### Surface Finish

3 The surface of the concrete should be inspected for defects, for conformity with the Specification and, where appropriate, for comparison with approved sample finishes.

Subject to the strength and durability of the concrete being unimpaired, the making good of surface defects may be permitted, but the standard of acceptance should be appropriate to the Class and quality of the finish

specified and should ensure satisfactory performance and durability. On permanently exposed surfaces great care is essential in selecting the mix proportions to ensure that the final colour of the faced area blends with the parent concrete in the finished structure.

### Dimensional Accuracy

4 (05/01) The methods of measurement of dimensional accuracy, making allowance for specified tolerances, if any, should be agreed in advance of manufacture.

The effect of temperature, shrinkage and imposed load should be taken into account.

The positions of bars, tendons or ducts should be checked where these are visible or ascertainable by simple means (reference sub-Clause 2(ii) (d) of this Clause).

In the case of precast units, the checking of twist, bow, squareness and flatness may entail removal of the unit from its stacked position to a special measuring frame. Extensive checking of units in this manner may materially affect the cost. The frequency and scope of measurement checks should therefore be strictly related to the production method, the standard of quality control at the place of casting, and the function that the unit has to fulfil.

When checking the camber or upward deflection due to prestress, the precast unit should be placed on proper bearings at full span and a central reference point should be provided level with the bearings. The amount of upward deflection to be expected at any stage should be assessed as described in BS 5400 : Part 4.

Alternative methods of checking include the use of dial gauges or measurements from a thin wire stretched across the bearings and tensioned sufficiently to take out the sag. Upward deflection is preferably measured on the underside.

### Load Tests on Individual Precast Units

5 (i) General. The load tests described in this Clause are intended as checks on the quality of the units and should not be used as a substitute for normal design procedures. Where members require special testing, such special testing procedures should be described in Appendix 17/4 and scheduled in Appendix 1/5.

Test loads should be applied and removed incrementally.

(ii) Non-destructive test. The unit should be supported at its designed points of support and loaded for 5 minutes with a load equivalent to the sum of the nominal dead

load plus 1.25 times the nominal imposed load. The deflection should then be recorded. The maximum deflection measured after application of the load should be in accordance with requirements defined by the designer. The recovery should be measured 5 minutes after the removal of the applied load and the load then reimposed. The percentage recovery after the second loading should be not less than that after the first loading nor less than 90% of the deflection recorded during the second loading. At no time during the test should the unit show any sign of weakness or faulty construction in the light of a reasonable interpretation of relevant data.

- (iii) Destructive test. The unit should be loaded while supported at its design points of support and should not fail at its ultimate design load within 15 minutes of the time when the test load becomes operative. A deflection exceeding one-fortieth of the span is regarded as failure of the unit.
- (iv) Special test. For very large units or units not readily amenable to tests (such as columns, the precast parts of composite beams, and members designed for continuity or fixity) the testing arrangements should be agreed before such units are cast.
- (v) Load testing of pretensioned beams. Load testing is not normally required and should only be embarked upon when the adequacy of the beams is in serious doubt.

### Load Tests of Structures or Parts of Structures

- 6 (i) General. The tests described in this Clause are intended as a check on structures other than those covered by NG 1727.5 where there is doubt regarding serviceability or strength.
- Test loads should be applied and removed incrementally.
- (ii) Age at test. The test should be carried out as soon as possible after the expiry of 28 days from the time of placing the concrete. When the test is for a reason other than the quality of the concrete in the structure being in doubt, the test may be carried out earlier provided that the concrete has already reached its specified characteristic strength.
- When testing prestressed concrete, allowance should be made for the effect of prestress at the time of testing being above

its final value.

- (iii) Test loads. The test loads to be applied for deflection and local damage are the appropriate design loads, ie. the nominal dead and imposed loads. When the ultimate limit state is being considered, the test load should be equivalent to the sum of the nominal dead load plus 1.25 times the nominal imposed load and should be maintained for a period of 24 hours. If any of the final dead load is not in position on the structure, compensating loads should be added as necessary.

During the tests, struts and bracing strong enough to support the whole load should be placed in position, leaving a gap under the members to be tested, and adequate precautions should be taken to safeguard persons in the vicinity of the structure.

- (iv) Measurements during the tests. Measurements of deflection and crack width should be taken immediately after the application of load and, in the case of the 24-hour sustained load test, at the end of the 24-hour loading period, after removal of the load and after the 24-hour recovery period. Sufficient measurements should be taken to enable side effects to be taken into account. Temperature and weather conditions should be recorded during the test.
- (v) Assessment of results. In assessing the serviceability of a structure or part of a structure following a loading test, the possible effects of variation in temperature and humidity during the period of the test should be considered.

The following recommendations should be met:

- (a) For reinforced concrete structures the maximum width of any crack measured immediately on application of the test load for local damage should not be more than two thirds of the value for the serviceability limit state of cracking given in BS 5400 : Part 4. For prestressed concrete structures or elements considered under Class 1 or Class 2, no visible cracks should occur under the test load for local damage.
- (b) For members spanning between two supports, the deflection measured immediately after application of the test load for deflection should be not more



than the specified value. Limits should be agreed before testing cantilevered portions of structures.

- (c) If, within 24 hours of the removal of the test load for the ultimate limit state as calculated in NG 1727.6(iii), a reinforced concrete structure does not show a recovery of at least 75% of the maximum deflection shown during the 24 hours under load, the loading should be repeated. The structure should be considered to have failed to pass the test if the recovery after the second loading is not at least 75% of the maximum deflection shown during the second loading.
- (d) If, within 24 hours of the removal of the test load for the ultimate limit state as calculated in NG 1727.6(iii), a prestressed concrete structure or member, considered under Class 1 or Class 2 does not show a recovery of at least 85% of the maximum deflection shown during the 24 hours under load, the loading should be repeated. The structure or member should be considered to have failed to pass the test if the recovery after the second loading is not at least 85% of the maximum deflection shown during the second loading.

WITHDRAWN

## NG SAMPLE APPENDIX 17/1: CONCRETE - CLASSIFICATION OF MIXES

	Mix Reference		
*Ordinary or Special Concrete (O or S)			
*Class of Concrete (Grade/Max. Agg. Size)			
*Minimum Cement Content (kg/m <sup>3</sup> )			
*Maximum Free Water/Cement Ratio			
Required Workability			
Max. Cement Content (kg/m <sup>3</sup> ) [See NG 1704.3]			
*Required Type and Class of Cement			
Required Source/Special Type of Aggregate			
Required Admixture			
Air Entrainment Required [YES/NO]			
Min. or Max. Temp. of Fresh Concrete °C			
Sampling and Testing	†	†	†
Other Requirements			

[Notes to compiler:

i) For ordinary structural concrete only information indicated by \* need be specified.

In appropriate circumstances any of the above information may be included, but great care should be taken to ensure that the requirements specified do not conflict with each other.

ii) Where admixtures will be acceptable as constituents of a Contractor's designed mix, the mix should be identified as Special Concrete.

† Cross-reference should be made to Appendix 1/5 or 1/6 as appropriate.]

## NG SAMPLE APPENDIX 17/2: CONCRETE - IMPREGNATION SCHEDULE

[Notes to compiler: Areas to be impregnated should be scheduled. If considered preferable the schedule can be placed on a Drawing and this Appendix should cross-refer.]

## NG SAMPLE APPENDIX 17/3: CONCRETE - SURFACE FINISHES

*[Note to compiler: Include here:]*

- 1 Requirements for Contract-specific surface finishes [1708.4] *[cross-referring to the Drawings as appropriate.]*
- 2 Requirements for trial panels [1708.1].
- 3 Positions where internal ties are permitted (other than in rebates) for Class F4 finish [1708.4(i)].
- 4 Locations where a regular pattern of formwork joints is unnecessary [1708.4(i)].

## NG SAMPLE APPENDIX 17/4 : CONCRETE - GENERAL

*[Note to compiler: This should include:]*

- 1 Requirements for concrete if different from the requirements of sub-Clause 1701.1.
- 2 Whether the use of cement other than to Clause 1702.1 is permitted [1703.1].
- 3 Requirements for lightweight aggregate if different from the requirements of sub-Clause 1703.2.
- 4 Requirements for admixtures if different from the requirements of sub-Clause 1703.4(i).
- 5 Requirements for sampling and testing if different from the requirements of sub-Clause 1707.1. Whether special testing is required [1707.2(iii)]. *[Cross-reference should be made in Appendix 1/5 or 1/6 as appropriate].*
- 6 References to drawings which show lifting and support points [1710.8(ii) and (iii)].
- 7 (02/03) Locations requiring stainless steel wire other than those described in sub-Clause 1714.1.
- 8 (02/03) Requirements for tolerance if different from the requirements of sub-Clause 1723.1.
- 9 (02/03) Requirements for time of stressing if different from the requirements of sub-Clauses 1724.3(ii) and 1724.4(iv).
- 10 (02/03) Requirements for protection of prestressing tendons [1725.1].
- 11 (02/03) Requirements for inspection and testing of structures and components [1727.1]. *[Guidance is given in NG 1727. Tests should be scheduled in Appendix 1/5].*
- 12 (02/03) Requirements for permanent formwork [1710.2(iv)].
- 13 (02/03) Requirements for assembly and erection of precast concrete members [1710.8(iv)].
- 14 (02/03) Whether type 1 or type 2 deformed carbon steel/stainless steel plain or ribbed bars are required [1712.7].
- 15 (02/03) Requirements for construction joints [1710.1].
- 16 (02/03) Whether retarding agents may be used [1710.1(ii)].
- 17 (02/03) Whether welding of reinforcement other than steel fabric reinforcement is permitted [1717.1].

# NG SAMPLE APPENDIX 17/5: (05/02) BURIED CONCRETE

[Note to compiler:

The following information should be completed for each structure, or group of structures, and applies only for buried concrete or partially buried concrete, ie. with one or more faces in contact with natural or disturbed ground or imported backfill.]

<p><b>STRUCTURE NAME OR LOCATION</b> <i>[a separate appendix should be provided for each structure or location with varying conditions or design constraints - identical conditions and constraints may be grouped together in one appendix]</i></p>	
<p><b>ACEC CLASS FOR SITE</b> <i>[derived from Table 17/5]</i></p>	
<p><b>STRUCTURAL PERFORMANCE LEVEL</b> <i>[High, normal or low] [derived from Table 17/6]</i></p>	
<p><b>DESIGN CHEMICAL CLASS</b> <i>[derived from the ACEC Class determined by assessment of ground conditions, together with the Structural Performance Level and the concrete section thickness and adjusted as necessary by reference to the footnotes to Table 17/7 and NG 1704.6(vi) for increase in concrete quality when used as an Additional Protective Measure; specification of 'starred' or 'double-starred' DC Classes; relaxation of one DC Class where permitted when concrete is surface-carbonated]</i></p>	
<p><b>OTHER REQUIREMENTS AND DESIGN CONSTRAINTS</b> <i>[eg Limitations on drainage, Additional Protective Measures required etc]</i></p>	

# NG SAMPLE APPENDIX 17/6 : (05/01) GROUTING AND DUCT SYSTEMS FOR POST-TENSIONED TENDONS

## TENDON REFERENCE:

*[Note to compiler: complete this for each different group or type of tendons]*

## GROUT DEFINITION:

Grout type: [Common] [Special]  
Maximum water/cement ratio: [0.40] [0.35]

## REQUIREMENTS FOR TRIALS/TESTS:

Full-scale grouting trials required: [Yes/No]  
Drawing Reference: .....  
*[full details including location of cuts should be defined on drawing]*

Time at which trials are to be carried out (days before planned use in the permanent works): [56 days]

*[Note to compiler: Optional additional testing requirements to prove protection against ingress of contaminants are given in Section 5 of the Concrete Society Technical Report 47 - Durable Bonded Post-Tensioned Concrete Bridges. Availability of compliant duct components should be discussed with manufacturers, and tests interpreted in accordance with Section 3.2A of the report.]*

Required duct assembly testing pressure: [0.01 N/mm<sup>2</sup>]  
Minimum duct wall thickness as manufactured: [2.0 mm]  
Minimum duct wall thickness after tensioning: [1.5 mm]  
Minimum duct to concrete ultimate bond length: [40 diameters]

## REQUIREMENTS FOR DUCT SYSTEM:

Distance beyond crests to next vent: *[Horizontally, to the point where the duct is half the diameter lower than at the crest, or 1m, whichever is the lesser]*

Maximum vent spacing [15m]  
Minimum vent height above highest point [500mm]  
Other requirements [-]

## Requirements for Grouting:

Maximum rate of grouting of ducts [10 m/min]  
Minimum volume of grout expelled after visual test [5 litres]

*[Note: Default values shown in brackets]*

# NATIONAL ALTERATIONS OF THE OVERSEEING ORGANISATION OF SCOTLAND

## NG 1703 SE (05/01) Concrete-Special Structural - Constituent Materials

### Cement

1 NG 1702.1 also applies.

### Aggregates

2 NG 1702.2 also applies to aggregates for special structural concrete. In addition the moisture content of lightweight aggregates can vary considerably, and values of up to 25% have been recorded. The use of a microwave oven may prove beneficial in quickly establishing the moisture content.

Lightweight aggregates may continue to absorb water from the mix and consideration may have to be given to allowing addition of water for workability.

It should be noted that the vibration characteristics of lightweight aggregate concrete may need special techniques to ensure good compaction and finishes.

### Admixtures

3 (i) (05/01) General. Admixtures should be specified by type and effect.

Admixtures should never be regarded as an alternative for good concreting practice and should never be used indiscriminately.

Many admixtures are highly active chemicals and may impart undesirable as well as desirable properties to the hardened concrete; their suitability should generally be verified by trial mixes. The trial mix should contain cement of the same make and from the same source as that intended to be used for the Permanent Works. If two or more admixtures are thought to be required in any one mix, the manufacturer of each should be consulted. The trials should confirm that the admixture is compatible with all the other constituents of the concrete mix and show whether it accelerates or retards the setting time and any loss of workability.

Only in exceptional circumstances, for example in hot weather, should retarders be used in structural concrete. Consideration may be given to their use in grouts for

prestressing tendons, especially in hot weather (see NG 1711.1).

(ii) (05/02) Air-entraining agents. Air-entraining agents used to entrain controlled percentages of air in the concrete generally improve its durability and in particular its resistance to damage caused by freezing and thawing.

All structural concrete in bridge decks and parapet edge beams, with the exception of prestressed concrete should be grade C40 and contain air entrainment as specified in Clauses 1703.4 and 1707.4. If a higher or lower grade is proposed, this should be agreed with the Overseeing Organisation.

For special structural concrete containing entrained air, the addition of 1% air content to the mix can reduce the compressive strength of the concrete by approximately 5%, but if the water/cement ratio is reduced to take account of the improved workability, the cement content may be kept constant for up to 5% air entrainment with only marginal loss of strength.

The carbon contained in pulverized-fuel ash and certain pigments can substantially reduce the effectiveness of air-entraining agents. This does not usually create a problem but care may have to be taken when using these materials. In some cases it may be necessary to increase appreciably the amount of agent used. The amount of air entrained in a concrete mix can also be affected by many other factors, among which are:

- (a) Type and amount of admixture used.
- (b) Consistency of the mix.
- (c) Mix proportions.
- (d) Type and grading of the aggregate.
- (e) The length of time for which the concrete is mixed.
- (f) Temperature. In the range 10°C to 30°C an increase of 10°C can reduce the amount of entrained air by about 25%.
- (g) The cement type, source, fineness and cement content of the mix.

Recommended average air contents of fresh concrete should be maintained within the limits specified irrespective of mixing time and temperature (see NG 1707.5).

Entrained air will increase the cohesiveness of fresh concrete and this should be taken into account in the design of the mix and in the placing and compaction of the concrete.

WITHHOLD DRAWM